


# **Argon**®

COLOR FORMULATING GUIDE



**Argon** MIXING COLORS



COLOR FORMULATING GUIDE

***Argon<sup>®</sup>MIXING COLORS***

***HI-GLOSS VINYL  
35.000 E***

# Argon® MIXING COLORS



Le formulazioni usate in questa guida sono state studiate per fornire le simulazioni dei colori PANTONE® usando i colori **Argon® MIXING COLORS**.

Le formulazioni sono state prodotte su PVC bianco utilizzando inchiostro non diluito, un telaio tesato a120 fili/cm e spremitore 70 shores.

NONOSTANTE LE FORMULAZIONI VENGANO PRODOTTE CON LA MASSIMA ATTENZIONE, L'UTILIZZO DI SUPPORTI DIVERSI O LA VARIAZIONE DELLE CONDIZIONI DI STAMPA POSSONO INFLUENZARE IL COLORE FINALE. ARGON NON SI ASSUME RESPONSABILITÀ PER IL COLORE REALE OTTENUTO. PER QUESTO MOTIVO, TUTTE LE FORMULAZIONI DEVONO ESSERE PROVATE PRIMA DEL CICLO DI PRODUZIONE PER ASSICURARSI DELLA PRECISIONE DEL COLORE.

Tutte le formule sono fornite in peso ed utilizzano i seguenti colori base **Argon® MIXING COLORS**

---

**P200**                      *AMC Primrose Yellow*

---

**P202**                      *AMC Chrome Yellow*

---

**P301**                      *AMC Orange*

---

**P303**                      *AMC Red*

---

**P305**                      *AMC Carmin Red*

---

**P342**                      *AMC Pink*

---

**P404**                      *AMC Brilliant Blue*

---

**P440**                      *AMC Violet*

---

**P500**                      *AMC Green*

---

LA SUDETTA GAMMA SI COMPLETA ANCHE CON L'AGGIUNTA DI:

100	WHITE
700	BLACK
800	TRANSPARENT BASE

Argon S.r.l.'s color mixing ink formulations produce only simulations of PANTONE® Colors in this color reproduction method due to differences in ink film, opacity and pigment selection. The pigment selection used in blending inks may cause metamerism. Pantone, Inc. assumes no responsibility for formula accuracy. All trademarks used herein are either the property of Argon S.r.l., Pantone, Inc. or their respective companies. Portions (C) Pantone, Inc. 1991.

ARGON S.r.l. Strada Statale 234 n° 37  
Tel. +39 (0) 377/960.1 - Fax +39 (0) 377/86330  
26864 Ospedaletto Lodigiano (LO) ITALY  
<http://www.argon.it>  
E-mail: [info.argon@argon.it](mailto:info.argon@argon.it)

# Argon® MIXING COLORS



The formulations listed in this guide have been studied to achieve the simulations of PANTONE® Colors with the use of **Argon® MIXING COLORS** basic colors.

They have been printed with undiluted ink on white PVC, using a 120T/cm fabric and a 70 shore squeegee.

Although special care has been taken in reproducing the color simulations, the use of different substrates or any changes in printing conditions can influence the final color. Therefore, Argon assumes no responsibility for the real color achieved. For this reason, we suggest to test all the formulations prior to each production run, in order to verify the color accuracy.

All the formulations are given in weight and have been prepared with the use of the following **Argon® MIXING COLORS** basic colors:

---

**P200** AMC Primrose Yellow

---

**P202** AMC Chrome Yellow

---

**P301** AMC Orange

---

**P303** AMC Red

---

**P305** AMC Carmin Red

---

**P342** AMC Pink

---

**P404** AMC Brilliant Blue

---

**P440** AMC Violet

---

**P500** AMC Green

---

TO THE ABOVE BASIC SERIES, THE FOLLOWING ITEMS HAVE TO BE ADDED:

100	WHITE
700	BLACK
800	TRANSPARENT BASE

Argon S.r.l.'s color mixing ink formulations produce only simulations of PANTONE® Colors in this color reproduction method due to differences in ink film, opacity and pigment selection. The pigment selection used in blending inks may cause metamerism. Pantone, Inc. assumes no responsibility for formula accuracy. All trademarks used herein are either the property of Argon s.r.l., Pantone, Inc. or their respective companies. Portions (C) Pantone, Inc. 1991.

Die vorliegende Formelsammlung schließt die Rezepte ein, die ausdrücklich für die Anwendung der **Argon® MIXING COLORS** Farben als Simulation der Pantone® Farben ausgewählt wurden. Die Rezepte wurden durch ein 120 Fäden/cm. Gewebe auf weiße PVC Folie und 70 Sh Härte Rakel gedruckt.

Die benutzten Farben waren ohne Verdünnung.

Wir unterstreichen, daß andere Bedruckstoffe oder Änderungen der Druckparameter das Farbtoneergebnis beeinflussen können. Argon übernimmt daher keine Verantwortung für die Genauigkeit der hergestellten Farbtöne. Zu diesem Zweck sollen alle Farben vor der ersten Produktionsverwendung geprüft werden.

Jede Rezeptur ist in Gewicht vorgeschlagen, mit folgenden **Argon® MIXING COLORS** Basisfarben.

---

**P200** AMC Primrose Yellow

---

**P202** AMC Chrome Yellow

---

**P301** AMC Orange

---

**P303** AMC Red

---

**P305** AMC Carmin Red

---

**P342** AMC Pink

---

**P404** AMC Brilliant Blue

---

**P440** AMC Violet

---

**P500** AMC Green

---

DIE OBENGENNANTE FARBTÖNE SOLLTEN MIT FOLGENDEN FARBEN VERVOLLSTÄNDIGEN SEIN:

100	WHITE
700	BLACK
800	TRANSPARENT BASE

ARGON S.r.l. Strada Statale 234 n° 37  
Tel. +39 (0) 377/960.1 - Fax +39 (0) 377/86330  
26864 Ospedaletto Lodigiano (LO) ITALY  
<http://www.argon.it>  
E-mail: [info.argon@argon.it](mailto:info.argon@argon.it)

# Argon® MIXING COLORS



Las formulaciones ilustradas en esta guía, han sido estudiadas para ofrecer simulaciones de los colores Pantone® utilizando los colores **Argon® MIXING COLORS**. Las formulaciones han sido aplicadas sobre PVC blanco, utilizando tinta sin diluir, malla de 120 hilos y rascle con goma de 70 Shore.

A pesar de que las fórmulas se compongan con el mayor cuidado, el empleo de las mismas sobre diferentes soportes, o la variación de las condiciones de impresión, pueden influir en el efecto final del color.

Argon no se responsabiliza por el color real conseguido. Por ello, todas las formulaciones deben ser probadas previamente antes del ciclo de producción, para asegurarse de la precisión en la tonalidad del color.

Todas las formulaciones son por porcentajes de peso usando los siguientes colores base: **Argon® MIXING COLORS**

---

**P200** AMC Primrose Yellow

---

**P202** AMC Chrome Yellow

---

**P301** AMC Orange

---

**P303** AMC Red

---

**P305** AMC Carmin Red

---

**P342** AMC Pink

---

**P404** AMC Brilliant Blue

---

**P440** AMC Violet

---

**P500** AMC Green

---

LA ANTERIOR GAMA SE COMPLETA CON LOS SIGUIENTES PRODUCTOS:

- 100 WHITE
- 700 BLACK
- 800 TRANSPARENT BASE

Argon S.r.l.'s color mixing ink formulations produce only simulations of PANTONE® Colors in this color reproduction method due to differences in ink film, opacity and pigment selection. The pigment selection used in blending inks may cause metamerism. Pantone, Inc. assumes no responsibility for formula accuracy. All trademarks used herein are either the property of Argon s.r.l., Pantone, Inc. or their respective companies. Portions (C) Pantone, Inc. 1991.

Les formules contenues dans ce guide ont été conçues pour fournir les simulations des couleurs PANTONE® utilisant les couleurs **Argon® MIXING COLORS**. Les formules ont été imprimées sur du PVC blanc avec une encre non diluée, un écran de 120 fils/cm et une racle de 70 shores.

Bienque tous nos soins aient été apportés à l'élaboration de ces formules, l'emploi de supports différents, ou bien la variation des conditions d'impression peuvent influir sur la couleur finale obtenue. Argon n'est pas responsable des couleurs réelles obtenues. Pour cette raison, afin de vérifier la précision de la couleur, il est toujours souhaitable de réaliser des essais d'impression avant le tirage définitif.

Toutes les formules sont fournies en poids, à partir des couleurs de base **Argon® MIXING COLORS** suivantes:

---

**P200** AMC Primrose Yellow

---

**P202** AMC Chrome Yellow

---

**P301** AMC Orange

---

**P303** AMC Red

---

**P305** AMC Carmin Red

---

**P342** AMC Pink

---

**P404** AMC Brilliant Blue

---

**P440** AMC Violet

---

**P500** AMC Green

---

LA GAMME CI DESSUS ÉNUMÉRÉE SE COMPLÈTE DE:

- 100 WHITE
- 700 BLACK
- 800 TRANSPARENT BASE

ARGON S.r.l. Strada Statale 234 n° 37  
 Tel. +39 (0) 377/960.1 - Fax +39 (0) 377/86330  
 26864 Ospedaletto Lodigiano (LO) ITALY  
<http://www.argon.it>  
 E-mail: info.argon@argon.it

**COLOR FORMULATING GUIDE**

**Argon® MIXING COLORS**

**FORMULATIONS FOR SIMULATIONS  
OF PANTONE® COLORS**



	<b>Ink Code</b>	<b>Color Shade</b>	<b>Weight</b>	<b>Notes</b>
<b>PANTONE Yellow C</b>	100	WHITE	176,0	
	P200	AMC PRIMROSE YELLOW	784,0	
	P202	AMC CHROME YELLOW	40,0	
			1000,0	
<b>PANTONE Yellow 012 C</b>	100	WHITE	180,0	
	P200	AMC PRIMROSE YELLOW	698,0	
	P202	AMC CHROME YELLOW	122,0	
			1000,0	
<b>PANTONE Orange 021 C</b>	100	WHITE	201,0	
	P202	AMC CHROME YELLOW	457,0	
	P301	AMC ORANGE	342,0	
			1000,0	
<b>PANTONE Warm Red C</b>	800	TRANSPARENT BASE	530,0	
	100	WHITE	180,0	
	P301	AMC ORANGE	170,0	
	P303	AMC RED	120,0	
			1000,0	
<b>PANTONE Red 032 C</b>	800	TRANSPARENT BASE	490,0	
	100	WHITE	165,0	
	P301	AMC ORANGE	90,0	
	P303	AMC RED	255,0	
			1000,0	
<b>PANTONE Rubine Red C</b>	800	TRANSPARENT BASE	750,0	
	100	WHITE	50,0	
	P303	AMC RED	50,0	
	P305	AMC CARMIN RED	150,0	
			1000,0	
<b>PANTONE Rhodamine Red C</b>	800	TRANSPARENT BASE	618,0	
	P301	AMC ORANGE	5,0	
	P342	AMC PINK	377,0	
			1000,0	

**COLOR FORMULATING GUIDE**

**Argon® MIXING COLORS**

**FORMULATIONS FOR SIMULATIONS  
OF PANTONE® COLORS**



	<b>Ink Code</b>	<b>Color Shade</b>	<b>Weight</b>	<b>Notes</b>
<b>PANTONE Purple C</b>	800	TRANSPARENT BASE	658,0	
	P342	AMC PINK	315,0	
	P440	AMC VIOLET	27,0	
			1000,0	
<b>PANTONE Violet C</b>	800	TRANSPARENT BASE	833,0	
	P404	AMC BRILLIANT BLUE	7,0	
	P440	AMC VIOLET	160,0	
			1000,0	
<b>PANTONE Blue 072 C</b>	800	TRANSPARENT BASE	670,0	
	P404	AMC BRILLIANT BLUE	80,0	
	P440	AMC VIOLET	250,0	
			1000,0	
<b>PANTONE Reflex Blue C</b>	800	TRANSPARENT BASE	680,0	
	100	WHITE	20,0	
	P404	AMC BRILLIANT BLUE	180,0	
	P440	AMC VIOLET	120,0	
			1000,0	
<b>PANTONE Process Blue C</b>	800	TRANSPARENT BASE	770,0	
	100	WHITE	100,0	
	P404	AMC BRILLIANT BLUE	120,0	
	P500	AMC GREEN	10,0	
			1000,0	
<b>PANTONE Green C</b>	800	TRANSPARENT BASE	667,0	
	100	WHITE	100,0	
	P202	AMC CHROME YELLOW	3,0	
	P500	AMC GREEN	230,0	
			1000,0	
<b>PANTONE Black C</b>	100	WHITE	280,0	
	700	BLACK	314,0	
	P202	AMC CHROME YELLOW	146,0	
	P301	AMC ORANGE	260,0	
			1000,0	

**COLOR FORMULATING GUIDE**

**Argon® MIXING COLORS**

**FORMULATIONS FOR SIMULATIONS  
OF PANTONE® COLORS**



	<b>Ink Code</b>	<b>Color Shade</b>	<b>Weight</b>	<b>Notes</b>
<b>PANTONE 100 C</b>	800	TRANSPARENT BASE	193,6	
	100	WHITE	613,1	
	P200	AMC PRIMROSE YELLOW	187,8	
	P202	AMC CHROME YELLOW	4,8	
	P342	AMC PINK	0,7	
			1000,0	
<b>PANTONE 101 C</b>	800	TRANSPARENT BASE	207,0	
	100	WHITE	408,0	
	P200	AMC PRIMROSE YELLOW	385,0	
			1000,0	
<b>PANTONE 102 C</b>	800	TRANSPARENT BASE	150,0	
	100	WHITE	70,0	
	P200	AMC PRIMROSE YELLOW	780,0	
			1000,0	
<b>PANTONE Yellow C</b>	100	WHITE	176,0	
	P200	AMC PRIMROSE YELLOW	784,0	
	P202	AMC CHROME YELLOW	40,0	
			1000,0	
<b>PANTONE 103 C</b>	700	BLACK	14,5	
	P200	AMC PRIMROSE YELLOW	951,5	
	P202	AMC CHROME YELLOW	34,0	
			1000,0	
<b>PANTONE 104 C</b>	100	WHITE	436,0	
	700	BLACK	15,0	
	P202	AMC CHROME YELLOW	542,0	
	P404	AMC BRILLIANT BLUE	7,0	
			1000,0	
<b>PANTONE 105 C</b>	100	WHITE	384,1	
	P202	AMC CHROME YELLOW	558,3	
	P305	AMC CARMIN RED	28,7	
	P404	AMC BRILLIANT BLUE	9,2	
	P500	AMC GREEN	19,7	
			1000,0	



**COLOR FORMULATING GUIDE**

**Argon® MIXING COLORS**

**FORMULATIONS FOR SIMULATIONS  
OF PANTONE® COLORS**



	<b>Ink Code</b>	<b>Color Shade</b>	<b>Weight</b>	<b>Notes</b>
<b>PANTONE 106 C</b>	800	TRANSPARENT BASE	9,3	
	100	WHITE	607,6	
	P200	AMC PRIMROSE YELLOW	381,5	
	P301	AMC ORANGE	1,6	
			1000,0	
<b>PANTONE 107 C</b>	100	WHITE	354,0	
	P200	AMC PRIMROSE YELLOW	644,0	
	P301	AMC ORANGE	2,0	
			1000,0	
<b>PANTONE 108 C</b>	100	WHITE	231,0	
	P200	AMC PRIMROSE YELLOW	766,0	
	P301	AMC ORANGE	3,0	
			1000,0	
<b>PANTONE 109 C</b>	100	WHITE	268,0	
	P200	AMC PRIMROSE YELLOW	519,0	
	P202	AMC CHROME YELLOW	212,7	
	P500	AMC GREEN	0,3	
			1000,0	
<b>PANTONE 110 C</b>	700	BLACK	10,0	
	P200	AMC PRIMROSE YELLOW	980,0	
	P301	AMC ORANGE	10,0	
			1000,0	
<b>PANTONE 111 C</b>	700	BLACK	34,0	
	P200	AMC PRIMROSE YELLOW	959,0	
	P301	AMC ORANGE	7,0	
			1000,0	
<b>PANTONE 112 C</b>	100	WHITE	426,2	
	P202	AMC CHROME YELLOW	531,4	
	P305	AMC CARMIN RED	19,3	
	P500	AMC GREEN	23,1	
			1000,0	

**COLOR FORMULATING GUIDE**

**Argon® MIXING COLORS**

**FORMULATIONS FOR SIMULATIONS  
OF PANTONE® COLORS**



	<b>Ink Code</b>	<b>Color Shade</b>	<b>Weight</b>	<b>Notes</b>
<b>PANTONE 113 C</b>	100	WHITE	573,8	
	P200	AMC PRIMROSE YELLOW	422,2	
	P301	AMC ORANGE	3,6	
	P303	AMC RED	0,4	
			1000,0	
<b>PANTONE 114 C</b>	100	WHITE	548,0	
	P200	AMC PRIMROSE YELLOW	448,0	
	P301	AMC ORANGE	4,0	
			1000,0	
<b>PANTONE 115 C</b>	100	WHITE	485,0	
	P200	AMC PRIMROSE YELLOW	512,0	
	P301	AMC ORANGE	3,0	
			1000,0	
<b>PANTONE 116 C</b>	100	WHITE	574,9	
	P202	AMC CHROME YELLOW	421,1	
	P301	AMC ORANGE	3,3	
	P500	AMC GREEN	0,7	
			1000,0	
<b>PANTONE 117 C</b>	800	TRANSPARENT BASE	670,0	
	100	WHITE	12,0	
	700	BLACK	26,0	
	P202	AMC CHROME YELLOW	292,0	
			1000,0	
<b>PANTONE 118 C</b>	800	TRANSPARENT BASE	761,0	
	100	WHITE	25,0	
	700	BLACK	34,0	
	P202	AMC CHROME YELLOW	180,0	
			1000,0	
<b>PANTONE 119 C</b>	100	WHITE	407,7	
	700	BLACK	56,5	
	P202	AMC CHROME YELLOW	535,8	
			1000,0	

**COLOR FORMULATING GUIDE**

**Argon® MIXING COLORS**

**FORMULATIONS FOR SIMULATIONS  
OF PANTONE® COLORS**



	<b>Ink Code</b>	<b>Color Shade</b>	<b>Weight</b>	<b>Notes</b>
<b>PANTONE 120 C</b>	800	TRANSPARENT BASE	253,0	
	100	WHITE	612,7	
	P200	AMC PRIMROSE YELLOW	129,8	
	P301	AMC ORANGE	3,9	
	P303	AMC RED	0,6	
			1000,0	
<b>PANTONE 121 C</b>	800	TRANSPARENT BASE	159,5	
	100	WHITE	611,0	
	P200	AMC PRIMROSE YELLOW	224,0	
	P301	AMC ORANGE	2,5	
	P303	AMC RED	3,0	
			1000,0	
<b>PANTONE 122 C</b>	100	WHITE	595,3	
	P200	AMC PRIMROSE YELLOW	396,0	
	P301	AMC ORANGE	5,4	
	P303	AMC RED	3,3	
			1000,0	
<b>PANTONE 123 C</b>	100	WHITE	380,0	
	P200	AMC PRIMROSE YELLOW	606,1	
	P301	AMC ORANGE	11,6	
	P303	AMC RED	2,3	
			1000,0	
<b>PANTONE 124 C</b>	100	WHITE	457,0	
	700	BLACK	7,0	
	P202	AMC CHROME YELLOW	530,0	
	P303	AMC RED	6,0	
			1000,0	
<b>PANTONE 125 C</b>	100	WHITE	430,5	
	700	BLACK	24,5	
	P202	AMC CHROME YELLOW	531,0	
	P303	AMC RED	14,0	
			1000,0	
<b>PANTONE 126 C</b>	100	WHITE	481,2	
	700	BLACK	28,4	
	P202	AMC CHROME YELLOW	479,3	
	P303	AMC RED	11,1	
			1000,0	

**COLOR FORMULATING GUIDE**

**Argon® MIXING COLORS**

**FORMULATIONS FOR SIMULATIONS  
OF PANTONE® COLORS**



	<b>Ink Code</b>	<b>Color Shade</b>	<b>Weight</b>	<b>Notes</b>
<b>PANTONE 1205 C</b>	800	TRANSPARENT BASE	399,6	
	100	WHITE	572,2	
	P200	AMC PRIMROSE YELLOW	25,5	
	P301	AMC ORANGE	1,4	
	P303	AMC RED	1,3	
			1000,0	
<b>PANTONE 1215 C</b>	800	TRANSPARENT BASE	296,8	
	100	WHITE	597,9	
	P200	AMC PRIMROSE YELLOW	98,9	
	P301	AMC ORANGE	2,0	
	P303	AMC RED	4,4	
			1000,0	
<b>PANTONE 1225 C</b>	100	WHITE	552,0	
	P200	AMC PRIMROSE YELLOW	432,0	
	P301	AMC ORANGE	7,5	
	P303	AMC RED	8,5	
			1000,0	
<b>PANTONE 1235 C</b>	100	WHITE	661,4	
	P200	AMC PRIMROSE YELLOW	51,0	
	P202	AMC CHROME YELLOW	268,5	
	P301	AMC ORANGE	11,8	
	P303	AMC RED	7,3	
			1000,0	
<b>PANTONE 1245 C</b>	100	WHITE	612,5	
	700	BLACK	15,7	
	P202	AMC CHROME YELLOW	360,0	
	P342	AMC PINK	11,8	
			1000,0	
<b>PANTONE 1255 C</b>	100	WHITE	515,1	
	700	BLACK	37,2	
	P202	AMC CHROME YELLOW	424,6	
	P342	AMC PINK	23,1	
			1000,0	
<b>PANTONE 1265 C</b>	100	WHITE	380,0	
	700	BLACK	50,0	
	P202	AMC CHROME YELLOW	517,0	
	P342	AMC PINK	53,0	
			1000,0	

**COLOR FORMULATING GUIDE**

**Argon® MIXING COLORS**

**FORMULATIONS FOR SIMULATIONS  
OF PANTONE® COLORS**



	<b>Ink Code</b>	<b>Color Shade</b>	<b>Weight</b>	<b>Notes</b>
<b>PANTONE 127 C</b>	800	TRANSPARENT BASE	239,6	
	100	WHITE	611,1	
	P200	AMC PRIMROSE YELLOW	139,6	
	P202	AMC CHROME YELLOW	7,6	
	P305	AMC CARMIN RED	2,1	
			1000,0	
<b>PANTONE 128 C</b>	800	TRANSPARENT BASE	85,0	
	100	WHITE	597,4	
	P200	AMC PRIMROSE YELLOW	315,5	
	P305	AMC CARMIN RED	2,1	
				1000,0
<b>PANTONE 129 C</b>	100	WHITE	496,0	
	P200	AMC PRIMROSE YELLOW	499,0	
	P305	AMC CARMIN RED	5,0	
				1000,0
<b>PANTONE 130 C</b>	100	WHITE	465,1	
	P202	AMC CHROME YELLOW	526,2	
	P305	AMC CARMIN RED	7,9	
	P404	AMC BRILLIANT BLUE	0,8	
				1000,0
<b>PANTONE 131 C</b>	100	WHITE	437,0	
	P202	AMC CHROME YELLOW	546,0	
	P305	AMC CARMIN RED	13,0	
	P404	AMC BRILLIANT BLUE	4,0	
				1000,0
<b>PANTONE 132 C</b>	100	WHITE	375,0	
	P202	AMC CHROME YELLOW	598,0	
	P305	AMC CARMIN RED	17,0	
	P404	AMC BRILLIANT BLUE	10,0	
				1000,0
<b>PANTONE 133 C</b>	100	WHITE	400,0	
	P202	AMC CHROME YELLOW	510,0	
	P305	AMC CARMIN RED	63,0	
	P404	AMC BRILLIANT BLUE	27,0	
				1000,0

**COLOR FORMULATING GUIDE**

**Argon® MIXING COLORS**

**FORMULATIONS FOR SIMULATIONS  
OF PANTONE® COLORS**



	<b>Ink Code</b>	<b>Color Shade</b>	<b>Weight</b>	<b>Notes</b>
<b>PANTONE 134 C</b>	800	TRANSPARENT BASE	229,9	
	100	WHITE	617,9	
	P200	AMC PRIMROSE YELLOW	142,3	
	P301	AMC ORANGE	7,9	
	P303	AMC RED	2,0	
			1000,0	
<b>PANTONE 135 C</b>	800	TRANSPARENT BASE	80,4	
	100	WHITE	620,0	
	P200	AMC PRIMROSE YELLOW	283,5	
	P301	AMC ORANGE	11,8	
	P303	AMC RED	4,3	
			1000,0	
<b>PANTONE 136 C</b>	100	WHITE	440,0	
	P200	AMC PRIMROSE YELLOW	535,5	
	P301	AMC ORANGE	19,2	
	P303	AMC RED	5,3	
			1000,0	
<b>PANTONE 137 C</b>	100	WHITE	536,0	
	P202	AMC CHROME YELLOW	420,0	
	P301	AMC ORANGE	36,0	
	P303	AMC RED	8,0	
			1000,0	
<b>PANTONE 138 C</b>	100	WHITE	418,0	
	700	BLACK	9,0	
	P202	AMC CHROME YELLOW	500,0	
	P301	AMC ORANGE	73,0	
			1000,0	
<b>PANTONE 139 C</b>	100	WHITE	432,0	
	700	BLACK	24,0	
	P202	AMC CHROME YELLOW	481,0	
	P301	AMC ORANGE	63,0	
			1000,0	
<b>PANTONE 140 C</b>	100	WHITE	443,4	
	700	BLACK	73,7	
	P202	AMC CHROME YELLOW	400,1	
	P301	AMC ORANGE	82,8	
			1000,0	

**COLOR FORMULATING GUIDE**

**Argon® MIXING COLORS**

**FORMULATIONS FOR SIMULATIONS  
OF PANTONE® COLORS**



	<b>Ink Code</b>	<b>Color Shade</b>	<b>Weight</b>	<b>Notes</b>
<b>PANTONE 1345 C</b>	800	TRANSPARENT BASE	319,6	
	100	WHITE	605,8	
	P200	AMC PRIMROSE YELLOW	65,0	
	P301	AMC ORANGE	7,5	
	P303	AMC RED	2,1	
			1000,0	
<b>PANTONE 1355 C</b>	800	TRANSPARENT BASE	229,0	
	100	WHITE	612,8	
	P200	AMC PRIMROSE YELLOW	140,0	
	P301	AMC ORANGE	14,0	
	P303	AMC RED	4,2	
			1000,0	
<b>PANTONE 1365 C</b>	100	WHITE	609,4	
	P200	AMC PRIMROSE YELLOW	361,4	
	P301	AMC ORANGE	23,2	
	P303	AMC RED	6,0	
			1000,0	
<b>PANTONE 1375 C</b>	100	WHITE	484,8	
	P202	AMC CHROME YELLOW	460,0	
	P301	AMC ORANGE	47,3	
	P303	AMC RED	7,9	
			1000,0	
<b>PANTONE 1385 C</b>	100	WHITE	431,3	
	700	BLACK	8,3	
	P202	AMC CHROME YELLOW	484,4	
	P303	AMC RED	76,0	
			1000,0	
<b>PANTONE 1395 C</b>	100	WHITE	398,3	
	700	BLACK	36,6	
	P202	AMC CHROME YELLOW	481,6	
	P303	AMC RED	83,5	
			1000,0	
<b>PANTONE 1405 C</b>	800	TRANSPARENT BASE	76,1	
	100	WHITE	250,5	
	700	BLACK	80,2	
	P202	AMC CHROME YELLOW	493,0	
	P303	AMC RED	100,2	
			1000,0	

**COLOR FORMULATING GUIDE**

**Argon® MIXING COLORS**

**FORMULATIONS FOR SIMULATIONS  
OF PANTONE® COLORS**



	<b>Ink Code</b>	<b>Color Shade</b>	<b>Weight</b>	<b>Notes</b>
<b>PANTONE 141 C</b>	800	TRANSPARENT BASE	95,5	
	100	WHITE	610,3	
	P200	AMC PRIMROSE YELLOW	284,0	
	P303	AMC RED	7,1	
	P305	AMC CARMIN RED	3,1	
			1000,0	
<b>PANTONE 142 C</b>	100	WHITE	475,7	
	P200	AMC PRIMROSE YELLOW	511,4	
	P303	AMC RED	7,8	
	P305	AMC CARMIN RED	5,1	
			1000,0	
<b>PANTONE 143 C</b>	100	WHITE	338,6	
	P200	AMC PRIMROSE YELLOW	646,9	
	P303	AMC RED	2,6	
	P305	AMC CARMIN RED	11,9	
			1000,0	
<b>PANTONE 144 C</b>	100	WHITE	381,0	
	700	BLACK	7,0	
	P202	AMC CHROME YELLOW	520,0	
	P301	AMC ORANGE	92,0	
			1000,0	
<b>PANTONE 145 C</b>	100	WHITE	368,0	
	700	BLACK	12,0	
	P202	AMC CHROME YELLOW	600,0	
	P305	AMC CARMIN RED	20,0	
			1000,0	
<b>PANTONE 146 C</b>	100	WHITE	339,0	
	700	BLACK	28,0	
	P202	AMC CHROME YELLOW	610,0	
	P305	AMC CARMIN RED	23,0	
			1000,0	
<b>PANTONE 147 C</b>	800	TRANSPARENT BASE	129,0	
	100	WHITE	380,0	
	700	BLACK	79,0	
	P202	AMC CHROME YELLOW	391,0	
	P305	AMC CARMIN RED	21,0	
			1000,0	



**COLOR FORMULATING GUIDE**

**Argon® MIXING COLORS**

**FORMULATIONS FOR SIMULATIONS  
OF PANTONE® COLORS**



	<b>Ink Code</b>	<b>Color Shade</b>	<b>Weight</b>	<b>Notes</b>
<b>PANTONE 148 C</b>	800	TRANSPARENT BASE	350,0	
	100	WHITE	584,0	
	P200	AMC PRIMROSE YELLOW	54,0	
	P301	AMC ORANGE	8,0	
	P303	AMC RED	4,0	
			1000,0	
<b>PANTONE 149 C</b>	800	TRANSPARENT BASE	308,3	
	100	WHITE	600,4	
	P200	AMC PRIMROSE YELLOW	72,4	
	P301	AMC ORANGE	11,4	
	P303	AMC RED	7,5	
			1000,0	
<b>PANTONE 150 C</b>	100	WHITE	605,7	
	P200	AMC PRIMROSE YELLOW	341,6	
	P301	AMC ORANGE	46,2	
	P303	AMC RED	6,5	
			1000,0	
<b>PANTONE 151 C</b>	100	WHITE	395,0	
	P202	AMC CHROME YELLOW	410,0	
	P301	AMC ORANGE	195,0	
			1000,0	
<b>PANTONE 152 C</b>	100	WHITE	360,0	
	700	BLACK	9,0	
	P202	AMC CHROME YELLOW	441,0	
	P301	AMC ORANGE	190,0	
			1000,0	
<b>PANTONE 153 C</b>	100	WHITE	383,5	
	700	BLACK	18,8	
	P202	AMC CHROME YELLOW	422,2	
	P301	AMC ORANGE	175,5	
			1000,0	
<b>PANTONE 154 C</b>	100	WHITE	300,0	
	700	BLACK	36,0	
	P202	AMC CHROME YELLOW	474,0	
	P301	AMC ORANGE	190,0	
			1000,0	

**COLOR FORMULATING GUIDE**



**Argon® MIXING COLORS**

**FORMULATIONS FOR SIMULATIONS  
OF PANTONE® COLORS**

	<b>Ink Code</b>	<b>Color Shade</b>	<b>Weight</b>	<b>Notes</b>
<b>PANTONE 1485 C</b>	800	TRANSPARENT BASE	294,6	
	100	WHITE	639,1	
	P202	AMC CHROME YELLOW	35,0	
	P301	AMC ORANGE	28,1	
	P342	AMC PINK	3,2	
			1000,0	
<b>PANTONE 1495 C</b>	800	TRANSPARENT BASE	96,5	
	100	WHITE	661,7	
	P202	AMC CHROME YELLOW	147,5	
	P301	AMC ORANGE	91,5	
	P342	AMC PINK	2,8	
			1000,0	
<b>PANTONE 1505 C</b>	100	WHITE	353,0	
	P202	AMC CHROME YELLOW	440,0	
	P301	AMC ORANGE	207,0	
			1000,0	
<b>PANTONE Orange 021 C</b>	100	WHITE	201,0	
	P202	AMC CHROME YELLOW	457,0	
	P301	AMC ORANGE	342,0	
			1000,0	
<b>PANTONE 1525 C</b>	800	TRANSPARENT BASE	655,0	
	100	WHITE	20,0	
	700	BLACK	25,0	
	P301	AMC ORANGE	300,0	
			1000,0	
<b>PANTONE 1535 C</b>	100	WHITE	185,0	
	700	BLACK	47,0	
	P202	AMC CHROME YELLOW	443,0	
	P301	AMC ORANGE	325,0	
			1000,0	
<b>PANTONE 1545 C</b>	100	WHITE	220,0	
	700	BLACK	120,0	
	P202	AMC CHROME YELLOW	400,0	
	P301	AMC ORANGE	200,0	
	P305	AMC CARMIN RED	60,0	
			1000,0	

**COLOR FORMULATING GUIDE**

**Argon® MIXING COLORS**

**FORMULATIONS FOR SIMULATIONS  
OF PANTONE® COLORS**



	<b>Ink Code</b>	<b>Color Shade</b>	<b>Weight</b>	<b>Notes</b>
<b>PANTONE 155 C</b>	800	TRANSPARENT BASE	367,0	
	100	WHITE	570,0	
	P200	AMC PRIMROSE YELLOW	56,0	
	P303	AMC RED	4,0	
	P305	AMC CARMIN RED	3,0	
			1000,0	
<b>PANTONE 156 C</b>	800	TRANSPARENT BASE	284,0	
	100	WHITE	593,0	
	P200	AMC PRIMROSE YELLOW	110,0	
	P303	AMC RED	9,0	
	P305	AMC CARMIN RED	4,0	
			1000,0	
<b>PANTONE 157 C</b>	100	WHITE	429,0	
	P200	AMC PRIMROSE YELLOW	529,6	
	P303	AMC RED	28,1	
	P305	AMC CARMIN RED	13,3	
			1000,0	
<b>PANTONE 158 C</b>	800	TRANSPARENT BASE	50,0	
	100	WHITE	395,0	
	P202	AMC CHROME YELLOW	500,0	
	P305	AMC CARMIN RED	55,0	
			1000,0	
<b>PANTONE 159 C</b>	100	WHITE	367,0	
	700	BLACK	8,0	
	P202	AMC CHROME YELLOW	570,0	
	P305	AMC CARMIN RED	55,0	
			1000,0	
<b>PANTONE 160 C</b>	100	WHITE	272,4	
	700	BLACK	28,6	
	P202	AMC CHROME YELLOW	637,2	
	P305	AMC CARMIN RED	61,8	
			1000,0	
<b>PANTONE 161 C</b>	800	TRANSPARENT BASE	137,0	
	100	WHITE	200,0	
	700	BLACK	72,0	
	P202	AMC CHROME YELLOW	517,0	
	P305	AMC CARMIN RED	74,0	
			1000,0	

**COLOR FORMULATING GUIDE**

**Argon® MIXING COLORS**

**FORMULATIONS FOR SIMULATIONS  
OF PANTONE® COLORS**



	<b>Ink Code</b>	<b>Color Shade</b>	<b>Weight</b>	<b>Notes</b>
<b>PANTONE 1555 C</b>	800	TRANSPARENT BASE	364,0	
	100	WHITE	580,0	
	P200	AMC PRIMROSE YELLOW	30,0	
	P301	AMC ORANGE	20,0	
	P303	AMC RED	6,0	
			1000,0	
<b>PANTONE 1565 C</b>	800	TRANSPARENT BASE	234,4	
	100	WHITE	632,5	
	P200	AMC PRIMROSE YELLOW	77,6	
	P301	AMC ORANGE	48,5	
	P303	AMC RED	7,0	
			1000,0	
<b>PANTONE 1575 C</b>	100	WHITE	534,0	
	P200	AMC PRIMROSE YELLOW	317,0	
	P301	AMC ORANGE	141,0	
	P303	AMC RED	8,0	
			1000,0	
<b>PANTONE 1585 C</b>	100	WHITE	570,8	
	P202	AMC CHROME YELLOW	186,2	
	P301	AMC ORANGE	230,7	
	P303	AMC RED	12,3	
			1000,0	
<b>PANTONE 1595 C</b>	100	WHITE	396,4	
	700	BLACK	14,4	
	P202	AMC CHROME YELLOW	240,2	
	P301	AMC ORANGE	349,0	
			1000,0	
<b>PANTONE 1605 C</b>	100	WHITE	393,0	
	700	BLACK	34,0	
	P202	AMC CHROME YELLOW	235,0	
	P301	AMC ORANGE	338,0	
			1000,0	
<b>PANTONE 1615 C</b>	800	TRANSPARENT BASE	65,0	
	100	WHITE	200,0	
	700	BLACK	50,0	
	P202	AMC CHROME YELLOW	150,0	
	P301	AMC ORANGE	535,0	
			1000,0	

**COLOR FORMULATING GUIDE**

**Argon® MIXING COLORS**

**FORMULATIONS FOR SIMULATIONS  
OF PANTONE® COLORS**



	<b>Ink Code</b>	<b>Color Shade</b>	<b>Weight</b>	<b>Notes</b>
<b>PANTONE 162 C</b>	800	TRANSPARENT BASE	470,0	
	100	WHITE	500,0	
	P200	AMC PRIMROSE YELLOW	13,0	
	P301	AMC ORANGE	11,0	
	P303	AMC RED	6,0	
			1000,0	
<b>PANTONE 163 C</b>	800	TRANSPARENT BASE	222,2	
	100	WHITE	637,5	
	P200	AMC PRIMROSE YELLOW	43,6	
	P301	AMC ORANGE	93,2	
	P303	AMC RED	3,5	
			1000,0	
<b>PANTONE 164 C</b>	100	WHITE	570,0	
	P200	AMC PRIMROSE YELLOW	173,5	
	P301	AMC ORANGE	256,5	
			1000,0	
<b>PANTONE 165 C</b>	100	WHITE	368,0	
	P202	AMC CHROME YELLOW	228,0	
	P301	AMC ORANGE	398,0	
	P303	AMC RED	6,0	
			1000,0	
<b>PANTONE 166 C</b>	100	WHITE	238,6	
	700	BLACK	7,2	
	P202	AMC CHROME YELLOW	229,3	
	P301	AMC ORANGE	524,9	
			1000,0	
<b>PANTONE 167 C</b>	100	WHITE	252,6	
	700	BLACK	22,8	
	P202	AMC CHROME YELLOW	230,6	
	P301	AMC ORANGE	494,0	
			1000,0	
<b>PANTONE 168 C</b>	100	WHITE	50,0	
	700	BLACK	70,0	
	P301	AMC ORANGE	880,0	
			1000,0	

**COLOR FORMULATING GUIDE**

**Argon® MIXING COLORS**

**FORMULATIONS FOR SIMULATIONS  
OF PANTONE® COLORS**



	<b>Ink Code</b>	<b>Color Shade</b>	<b>Weight</b>	<b>Notes</b>
<b>PANTONE 1625 C</b>	800	TRANSPARENT BASE	317,7	
	100	WHITE	617,6	
	P301	AMC ORANGE	51,3	
	P303	AMC RED	13,4	
			1000,0	
<b>PANTONE 1635 C</b>	800	TRANSPARENT BASE	234,0	
	100	WHITE	637,0	
	P301	AMC ORANGE	114,0	
	P303	AMC RED	15,0	
			1000,0	
<b>PANTONE 1645 C</b>	800	TRANSPARENT BASE	39,0	
	100	WHITE	650,0	
	P301	AMC ORANGE	300,0	
	P303	AMC RED	11,0	
			1000,0	
<b>PANTONE 1655 C</b>	800	TRANSPARENT BASE	30,0	
	100	WHITE	420,0	
	P202	AMC CHROME YELLOW	40,0	
	P301	AMC ORANGE	500,0	
	P303	AMC RED	10,0	
			1000,0	
<b>PANTONE 1665 C</b>	100	WHITE	369,0	
	700	BLACK	7,0	
	P202	AMC CHROME YELLOW	279,0	
	P301	AMC ORANGE	327,0	
	P305	AMC CARMIN RED	18,0	
			1000,0	
<b>PANTONE 1675 C</b>	100	WHITE	336,0	
	700	BLACK	30,0	
	P202	AMC CHROME YELLOW	320,0	
	P301	AMC ORANGE	269,0	
	P305	AMC CARMIN RED	45,0	
			1000,0	
<b>PANTONE 1685 C</b>	100	WHITE	235,7	
	700	BLACK	46,4	
	P202	AMC CHROME YELLOW	256,4	
	P301	AMC ORANGE	427,0	
	P305	AMC CARMIN RED	34,5	
			1000,0	

## COLOR FORMULATING GUIDE

# Argon® MIXING COLORS

### FORMULATIONS FOR SIMULATIONS OF PANTONE® COLORS



	Ink Code	Color Shade	Weight	Notes
<b>PANTONE 169 C</b>	800	TRANSPARENT BASE	472,5	
	100	WHITE	499,5	
	P301	AMC ORANGE	15,0	
	P303	AMC RED	13,0	
			1000,0	
<b>PANTONE 170 C</b>	800	TRANSPARENT BASE	231,8	
	100	WHITE	627,5	
	P301	AMC ORANGE	97,3	
	P303	AMC RED	43,4	
			1000,0	
<b>PANTONE 171 C</b>	800	TRANSPARENT BASE	365,0	
	100	WHITE	340,0	
	P301	AMC ORANGE	229,2	
	P303	AMC RED	65,8	
			1000,0	
<b>PANTONE 172 C</b>	800	TRANSPARENT BASE	525,0	
	100	WHITE	120,0	
	P301	AMC ORANGE	285,0	
	P303	AMC RED	70,0	
			1000,0	
<b>PANTONE 173 C</b>	800	TRANSPARENT BASE	207,0	
	100	WHITE	205,0	
	700	BLACK	10,0	
	P301	AMC ORANGE	565,0	
	P305	AMC CARMIN RED	13,0	
				1000,0
<b>PANTONE 174 C</b>	100	WHITE	306,0	
	700	BLACK	34,0	
	P202	AMC CHROME YELLOW	285,0	
	P301	AMC ORANGE	305,0	
	P305	AMC CARMIN RED	70,0	
			1000,0	
<b>PANTONE 175 C</b>	100	WHITE	200,0	
	700	BLACK	75,0	
	P202	AMC CHROME YELLOW	200,0	
	P301	AMC ORANGE	425,0	
	P305	AMC CARMIN RED	100,0	
			1000,0	

**COLOR FORMULATING GUIDE**

**Argon® MIXING COLORS**

**FORMULATIONS FOR SIMULATIONS  
OF PANTONE® COLORS**



	<b>Ink Code</b>	<b>Color Shade</b>	<b>Weight</b>	<b>Notes</b>
<b>PANTONE 176 C</b>	800	TRANSPARENT BASE	768,5	
	100	WHITE	188,6	
	P301	AMC ORANGE	11,0	
	P303	AMC RED	31,9	
			1000,0	
<b>PANTONE 177 C</b>	800	TRANSPARENT BASE	860,0	
	100	WHITE	60,0	
	P301	AMC ORANGE	10,0	
	P303	AMC RED	70,0	
			1000,0	
<b>PANTONE 178 C</b>	800	TRANSPARENT BASE	646,0	
	100	WHITE	205,0	
	P301	AMC ORANGE	36,0	
	P303	AMC RED	113,0	
			1000,0	
<b>PANTONE Warm Red C</b>	800	TRANSPARENT BASE	530,0	
	100	WHITE	180,0	
	P301	AMC ORANGE	170,0	
	P303	AMC RED	120,0	
			1000,0	
<b>PANTONE 179 C</b>	800	TRANSPARENT BASE	320,0	
	100	WHITE	201,0	
	700	BLACK	3,0	
	P301	AMC ORANGE	241,0	
	P342	AMC PINK	235,0	
				1000,0
<b>PANTONE 180 C</b>	100	WHITE	414,0	
	700	BLACK	14,0	
	P301	AMC ORANGE	502,0	
	P305	AMC CARMIN RED	70,0	
			1000,0	
<b>PANTONE 181 C</b>	800	TRANSPARENT BASE	100,0	
	100	WHITE	240,0	
	700	BLACK	50,0	
	P301	AMC ORANGE	530,0	
	P305	AMC CARMIN RED	80,0	
				1000,0



**COLOR FORMULATING GUIDE**

**Argon® MIXING COLORS**

**FORMULATIONS FOR SIMULATIONS  
OF PANTONE® COLORS**



	<b>Ink Code</b>	<b>Color Shade</b>	<b>Weight</b>	<b>Notes</b>
<b>PANTONE 1765 C</b>	800	TRANSPARENT BASE	700,0	
	100	WHITE	234,0	
	P301	AMC ORANGE	13,0	
	P342	AMC PINK	53,0	
			1000,0	
<b>PANTONE 1775 C</b>	800	TRANSPARENT BASE	570,0	
	100	WHITE	330,0	
	P301	AMC ORANGE	20,0	
	P342	AMC PINK	80,0	
			1000,0	
<b>PANTONE 1785 C</b>	800	TRANSPARENT BASE	750,0	
	100	WHITE	75,0	
	P301	AMC ORANGE	25,0	
	P303	AMC RED	150,0	
			1000,0	
<b>PANTONE 1788 C</b>	800	TRANSPARENT BASE	775,0	
	P301	AMC ORANGE	39,0	
	P303	AMC RED	183,0	
	P342	AMC PINK	3,0	
			1000,0	
<b>PANTONE 1795 C</b>	800	TRANSPARENT BASE	187,0	
	100	WHITE	170,0	
	700	BLACK	3,0	
	P301	AMC ORANGE	240,0	
	P342	AMC PINK	400,0	
			1000,0	
<b>PANTONE 1805 C</b>	800	TRANSPARENT BASE	241,0	
	100	WHITE	165,0	
	700	BLACK	19,0	
	P301	AMC ORANGE	220,0	
	P342	AMC PINK	355,0	
			1000,0	
<b>PANTONE 1815 C</b>	800	TRANSPARENT BASE	300,0	
	100	WHITE	80,0	
	700	BLACK	45,0	
	P301	AMC ORANGE	200,0	
	P342	AMC PINK	375,0	
			1000,0	

**COLOR FORMULATING GUIDE**

**Argon® MIXING COLORS**

**FORMULATIONS FOR SIMULATIONS  
OF PANTONE® COLORS**



	<b>Ink Code</b>	<b>Color Shade</b>	<b>Weight</b>	<b>Notes</b>
<b>PANTONE 1767 C</b>	800	TRANSPARENT BASE	419,0	
	100	WHITE	551,0	
	P301	AMC ORANGE	4,0	
	P303	AMC RED	26,0	
			1000,0	
<b>PANTONE 1777 C</b>	800	TRANSPARENT BASE	370,0	
	100	WHITE	400,0	
	P301	AMC ORANGE	30,0	
	P303	AMC RED	200,0	
			1000,0	
<b>PANTONE 1787 C</b>	800	TRANSPARENT BASE	514,0	
	100	WHITE	187,0	
	P301	AMC ORANGE	24,0	
	P303	AMC RED	275,0	
			1000,0	
<b>PANTONE Red 032 C</b>	800	TRANSPARENT BASE	490,0	
	100	WHITE	165,0	
	P301	AMC ORANGE	90,0	
	P303	AMC RED	255,0	
			1000,0	
<b>PANTONE 1797 C</b>	100	WHITE	281,0	
	700	BLACK	4,0	
	P301	AMC ORANGE	200,0	
	P303	AMC RED	515,0	
			1000,0	
<b>PANTONE 1807 C</b>	100	WHITE	244,0	
	700	BLACK	26,0	
	P301	AMC ORANGE	180,0	
	P303	AMC RED	550,0	
			1000,0	
<b>PANTONE 1817 C</b>	100	WHITE	150,0	
	700	BLACK	110,0	
	P301	AMC ORANGE	300,0	
	P305	AMC CARMIN RED	440,0	
			1000,0	

**COLOR FORMULATING GUIDE**

**Argon® MIXING COLORS**

**FORMULATIONS FOR SIMULATIONS  
OF PANTONE® COLORS**



	<b>Ink Code</b>	<b>Color Shade</b>	<b>Weight</b>	<b>Notes</b>
<b>PANTONE 182 C</b>	800	TRANSPARENT BASE	428,2	
	100	WHITE	538,2	
	P301	AMC ORANGE	6,8	
	P342	AMC PINK	26,8	
			1000,0	
<b>PANTONE 183 C</b>	800	TRANSPARENT BASE	570,0	
	100	WHITE	310,0	
	P301	AMC ORANGE	20,0	
	P342	AMC PINK	100,0	
			1000,0	
<b>PANTONE 184 C</b>	800	TRANSPARENT BASE	333,0	
	100	WHITE	396,0	
	P301	AMC ORANGE	59,0	
	P342	AMC PINK	212,0	
			1000,0	
<b>PANTONE 185 C</b>	800	TRANSPARENT BASE	640,0	
	100	WHITE	50,0	
	P301	AMC ORANGE	20,0	
	P303	AMC RED	290,0	
			1000,0	
<b>PANTONE 186 C</b>	100	WHITE	319,0	
	700	BLACK	1,0	
	P301	AMC ORANGE	500,0	
	P305	AMC CARMIN RED	180,0	
			1000,0	
<b>PANTONE 187 C</b>	100	WHITE	246,0	
	700	BLACK	14,0	
	P301	AMC ORANGE	480,0	
	P305	AMC CARMIN RED	260,0	
			1000,0	
<b>PANTONE 188 C</b>	800	TRANSPARENT BASE	670,0	
	100	WHITE	90,0	
	700	BLACK	40,0	
	P301	AMC ORANGE	100,0	
	P305	AMC CARMIN RED	100,0	
			1000,0	

**COLOR FORMULATING GUIDE**

**Argon® MIXING COLORS**

**FORMULATIONS FOR SIMULATIONS  
OF PANTONE® COLORS**



	<b>Ink Code</b>	<b>Color Shade</b>	<b>Weight</b>	<b>Notes</b>
<b>PANTONE 189 C</b>	800	TRANSPARENT BASE	549,0	
	100	WHITE	400,0	
	P301	AMC ORANGE	1,0	
	P303	AMC RED	50,0	
			1000,0	
<b>PANTONE 190 C</b>	800	TRANSPARENT BASE	370,0	
	100	WHITE	450,0	
	P303	AMC RED	180,0	
			1000,0	
<b>PANTONE 191 C</b>	800	TRANSPARENT BASE	350,0	
	100	WHITE	300,0	
	P303	AMC RED	300,0	
	P342	AMC PINK	50,0	
			1000,0	
<b>PANTONE 192 C</b>	800	TRANSPARENT BASE	550,0	
	100	WHITE	50,0	
	P303	AMC RED	300,0	
	P342	AMC PINK	100,0	
			1000,0	
<b>PANTONE 193 C</b>	100	WHITE	57,0	
	700	BLACK	11,0	
	P303	AMC RED	582,0	
	P342	AMC PINK	350,0	
			1000,0	
<b>PANTONE 194 C</b>	100	WHITE	126,0	
	700	BLACK	30,0	
	P303	AMC RED	594,0	
	P342	AMC PINK	250,0	
			1000,0	
<b>PANTONE 195 C</b>	800	TRANSPARENT BASE	310,0	
	100	WHITE	80,0	
	700	BLACK	60,0	
	P303	AMC RED	400,0	
	P342	AMC PINK	150,0	
			1000,0	

## COLOR FORMULATING GUIDE

# Argon® MIXING COLORS

### FORMULATIONS FOR SIMULATIONS OF PANTONE® COLORS



	Ink Code	Color Shade	Weight	Notes
<b>PANTONE 1895 C</b>	800	TRANSPARENT BASE	444,3	
	100	WHITE	526,9	
	P301	AMC ORANGE	2,2	
	P303	AMC RED	9,5	
	P342	AMC PINK	17,1	
			1000,0	
<b>PANTONE 1905 C</b>	800	TRANSPARENT BASE	369,3	
	100	WHITE	542,0	
	P301	AMC ORANGE	8,7	
	P342	AMC PINK	80,0	
			1000,0	
<b>PANTONE 1915 C</b>	800	TRANSPARENT BASE	270,0	
	100	WHITE	410,0	
	P303	AMC RED	230,0	
	P342	AMC PINK	90,0	
			1000,0	
<b>PANTONE 1925 C</b>	800	TRANSPARENT BASE	450,0	
	100	WHITE	110,0	
	P303	AMC RED	240,0	
	P342	AMC PINK	200,0	
			1000,0	
<b>PANTONE 1935 C</b>	100	WHITE	167,0	
	700	BLACK	3,0	
	P303	AMC RED	480,0	
	P342	AMC PINK	350,0	
			1000,0	
<b>PANTONE 1945 C</b>	100	WHITE	146,0	
	700	BLACK	16,0	
	P303	AMC RED	400,0	
	P342	AMC PINK	438,0	
			1000,0	
<b>PANTONE 1955 C</b>	800	TRANSPARENT BASE	412,0	
	100	WHITE	110,0	
	700	BLACK	18,0	
	P303	AMC RED	220,0	
	P342	AMC PINK	240,0	
			1000,0	

**COLOR FORMULATING GUIDE**

**Argon® MIXING COLORS**

**FORMULATIONS FOR SIMULATIONS  
OF PANTONE® COLORS**



	<b>Ink Code</b>	<b>Color Shade</b>	<b>Weight</b>	<b>Notes</b>
<b>PANTONE 196 C</b>	800	TRANSPARENT BASE	451,5	
	100	WHITE	529,9	
	P200	AMC PRIMROSE YELLOW	9,8	
	P303	AMC RED	3,9	
	P305	AMC CARMIN RED	4,9	
			1000,0	
<b>PANTONE 197 C</b>	800	TRANSPARENT BASE	365,8	
	100	WHITE	549,5	
	P200	AMC PRIMROSE YELLOW	38,4	
	P303	AMC RED	21,6	
	P305	AMC CARMIN RED	24,7	
			1000,0	
<b>PANTONE 198 C</b>	800	TRANSPARENT BASE	29,5	
	100	WHITE	578,0	
	P200	AMC PRIMROSE YELLOW	8,1	
	P303	AMC RED	378,1	
	P305	AMC CARMIN RED	6,3	
			1000,0	
<b>PANTONE 199 C</b>	100	WHITE	250,0	
	P303	AMC RED	750,0	
			1000,0	
<b>PANTONE 200 C</b>	100	WHITE	231,0	
	700	BLACK	4,0	
	P301	AMC ORANGE	315,0	
	P305	AMC CARMIN RED	450,0	
			1000,0	
<b>PANTONE 201 C</b>	100	WHITE	293,0	
	700	BLACK	15,0	
	P202	AMC CHROME YELLOW	100,0	
	P301	AMC ORANGE	100,0	
	P305	AMC CARMIN RED	492,0	
			1000,0	
<b>PANTONE 202 C</b>	100	WHITE	310,0	
	700	BLACK	30,0	
	P202	AMC CHROME YELLOW	50,0	
	P301	AMC ORANGE	300,0	
	P305	AMC CARMIN RED	310,0	
			1000,0	

**COLOR FORMULATING GUIDE**

**Argon® MIXING COLORS**

**FORMULATIONS FOR SIMULATIONS  
OF PANTONE® COLORS**



	<b>Ink Code</b>	<b>Color Shade</b>	<b>Weight</b>	<b>Notes</b>
<b>PANTONE 203 C</b>	800	TRANSPARENT BASE	430,0	
	100	WHITE	522,0	
	P200	AMC PRIMROSE YELLOW	13,0	
	P305	AMC CARMIN RED	9,0	
	P342	AMC PINK	26,0	
			1000,0	
<b>PANTONE 204 C</b>	100	WHITE	715,0	
	P200	AMC PRIMROSE YELLOW	50,0	
	P342	AMC PINK	235,0	
			1000,0	
<b>PANTONE 205 C</b>	800	TRANSPARENT BASE	150,0	
	100	WHITE	360,0	
	P200	AMC PRIMROSE YELLOW	75,0	
	P342	AMC PINK	415,0	
			1000,0	
<b>PANTONE 206 C</b>	800	TRANSPARENT BASE	610,0	
	100	WHITE	110,0	
	P303	AMC RED	170,0	
	P305	AMC CARMIN RED	110,0	
			1000,0	
<b>PANTONE 207 C</b>	100	WHITE	241,0	
	700	BLACK	9,0	
	P303	AMC RED	370,0	
	P305	AMC CARMIN RED	380,0	
			1000,0	
<b>PANTONE 208 C</b>	800	TRANSPARENT BASE	200,0	
	100	WHITE	222,0	
	700	BLACK	28,0	
	P303	AMC RED	180,0	
	P305	AMC CARMIN RED	370,0	
			1000,0	
<b>PANTONE 209 C</b>	800	TRANSPARENT BASE	650,0	
	100	WHITE	100,0	
	700	BLACK	35,0	
	P303	AMC RED	160,0	
	P305	AMC CARMIN RED	55,0	
			1000,0	

**COLOR FORMULATING GUIDE**

**Argon® MIXING COLORS**

**FORMULATIONS FOR SIMULATIONS  
OF PANTONE® COLORS**



	<b>Ink Code</b>	<b>Color Shade</b>	<b>Weight</b>	<b>Notes</b>
<b>PANTONE 210 C</b>	800	TRANSPARENT BASE	758,0	
	100	WHITE	172,0	
	P301	AMC ORANGE	6,0	
	P342	AMC PINK	64,0	
			1000,0	
<b>PANTONE 211 C</b>	800	TRANSPARENT BASE	556,3	
	100	WHITE	287,4	
	P301	AMC ORANGE	11,1	
	P342	AMC PINK	145,2	
			1000,0	
<b>PANTONE 212 C</b>	800	TRANSPARENT BASE	90,0	
	100	WHITE	423,0	
	P301	AMC ORANGE	36,0	
	P342	AMC PINK	451,0	
			1000,0	
<b>PANTONE 213 C</b>	800	TRANSPARENT BASE	575,0	
	P301	AMC ORANGE	25,0	
	P342	AMC PINK	400,0	
			1000,0	
<b>PANTONE 214 C</b>	100	WHITE	143,0	
	P303	AMC RED	188,0	
	P342	AMC PINK	669,0	
			1000,0	
<b>PANTONE 215 C</b>	800	TRANSPARENT BASE	121,0	
	100	WHITE	90,0	
	700	BLACK	17,0	
	P303	AMC RED	195,0	
	P342	AMC PINK	577,0	
			1000,0	
<b>PANTONE 216 C</b>	800	TRANSPARENT BASE	315,0	
	100	WHITE	90,0	
	700	BLACK	35,0	
	P301	AMC ORANGE	40,0	
	P342	AMC PINK	500,0	
	P303	AMC RED	20,0	
			1000,0	



**COLOR FORMULATING GUIDE**

**Argon® MIXING COLORS**

**FORMULATIONS FOR SIMULATIONS  
OF PANTONE® COLORS**



	<b>Ink Code</b>	<b>Color Shade</b>	<b>Weight</b>	<b>Notes</b>
<b>PANTONE 217 C</b>	800	TRANSPARENT BASE	473,0	
	100	WHITE	512,0	
	P200	AMC PRIMROSE YELLOW	5,0	
	P305	AMC CARMIN RED	10,0	
			1000,0	
<b>PANTONE 218 C</b>	800	TRANSPARENT BASE	459,0	
	100	WHITE	475,0	
	P200	AMC PRIMROSE YELLOW	8,0	
	P305	AMC CARMIN RED	58,0	
			1000,0	
<b>PANTONE 219 C</b>	800	TRANSPARENT BASE	655,4	
	100	WHITE	179,3	
	P200	AMC PRIMROSE YELLOW	12,9	
	P305	AMC CARMIN RED	152,4	
			1000,0	
<b>PANTONE Rubine Red C</b>	800	TRANSPARENT BASE	750,0	
	100	WHITE	50,0	
	P303	AMC RED	50,0	
	P305	AMC CARMIN RED	150,0	
			1000,0	
<b>PANTONE 220 C</b>	100	WHITE	40,0	
	700	BLACK	13,0	
	P303	AMC RED	120,0	
	P342	AMC PINK	827,0	
			1000,0	
<b>PANTONE 221 C</b>	700	BLACK	25,0	
	P303	AMC RED	175,0	
	P342	AMC PINK	800,0	
			1000,0	
<b>PANTONE 222 C</b>	800	TRANSPARENT BASE	307,0	
	100	WHITE	70,0	
	700	BLACK	43,0	
	P303	AMC RED	120,0	
	P342	AMC PINK	460,0	
			1000,0	

**COLOR FORMULATING GUIDE**

**Argon® MIXING COLORS**

**FORMULATIONS FOR SIMULATIONS  
OF PANTONE® COLORS**



	<b>Ink Code</b>	<b>Color Shade</b>	<b>Weight</b>	<b>Notes</b>
<b>PANTONE 223 C</b>	800	TRANSPARENT BASE	698,0	
	100	WHITE	220,0	
	P301	AMC ORANGE	2,0	
	P342	AMC PINK	80,0	
			1000,0	
<b>PANTONE 224 C</b>	800	TRANSPARENT BASE	487,0	
	100	WHITE	300,0	
	P301	AMC ORANGE	3,0	
	P342	AMC PINK	210,0	
			1000,0	
<b>PANTONE 225 C</b>	800	TRANSPARENT BASE	500,0	
	100	WHITE	100,0	
	P301	AMC ORANGE	7,0	
	P342	AMC PINK	393,0	
			1000,0	
<b>PANTONE 226 C</b>	800	TRANSPARENT BASE	165,0	
	100	WHITE	122,0	
	P303	AMC RED	55,0	
	P342	AMC PINK	658,0	
			1000,0	
<b>PANTONE 227 C</b>	100	WHITE	30,0	
	700	BLACK	22,0	
	P303	AMC RED	70,0	
	P342	AMC PINK	878,0	
			1000,0	
<b>PANTONE 228 C</b>	100	WHITE	95,0	
	700	BLACK	31,0	
	P305	AMC CARMIN RED	100,0	
	P342	AMC PINK	774,0	
			1000,0	
<b>PANTONE 229 C</b>	800	TRANSPARENT BASE	250,0	
	100	WHITE	120,0	
	700	BLACK	50,0	
	P303	AMC RED	100,0	
	P305	AMC CARMIN RED	80,0	
	P342	AMC PINK	400,0	
			1000,0	

**COLOR FORMULATING GUIDE**

**Argon® MIXING COLORS**

**FORMULATIONS FOR SIMULATIONS  
OF PANTONE® COLORS**



	<b>Ink Code</b>	<b>Color Shade</b>	<b>Weight</b>	<b>Notes</b>
<b>PANTONE 230 C</b>	800	TRANSPARENT BASE	647,0	
	100	WHITE	290,0	
	P301	AMC ORANGE	3,0	
	P342	AMC PINK	60,0	
			1000,0	
<b>PANTONE 231 C</b>	800	TRANSPARENT BASE	558,5	
	100	WHITE	267,0	
	P301	AMC ORANGE	4,5	
	P342	AMC PINK	170,0	
			1000,0	
<b>PANTONE 232 C</b>	800	TRANSPARENT BASE	463,9	
	100	WHITE	212,8	
	P301	AMC ORANGE	4,2	
	P342	AMC PINK	319,1	
			1000,0	
<b>PANTONE Rhodamine Red C</b>	800	TRANSPARENT BASE	618,0	
	P301	AMC ORANGE	5,0	
	P342	AMC PINK	377,0	
			1000,0	
<b>PANTONE 233 C</b>	800	TRANSPARENT BASE	170,0	
	100	WHITE	120,0	
	P305	AMC CARMIN RED	50,0	
	P342	AMC PINK	660,0	
			1000,0	
<b>PANTONE 234 C</b>	800	TRANSPARENT BASE	200,0	
	100	WHITE	60,0	
	700	BLACK	20,0	
	P305	AMC CARMIN RED	6,0	
	P342	AMC PINK	714,0	
			1000,0	
<b>PANTONE 235 C</b>	800	TRANSPARENT BASE	153,0	
	100	WHITE	90,0	
	700	BLACK	17,0	
	P305	AMC CARMIN RED	40,0	
	P342	AMC PINK	700,0	
			1000,00	

**COLOR FORMULATING GUIDE**

**Argon® MIXING COLORS**

**FORMULATIONS FOR SIMULATIONS  
OF PANTONE® COLORS**



	<b>Ink Code</b>	<b>Color Shade</b>	<b>Weight</b>	<b>Notes</b>
<b>PANTONE 236 C</b>	800	TRANSPARENT BASE	445,0	
	100	WHITE	500,0	
	P301	AMC ORANGE	1,0	
	P342	AMC PINK	54,0	
			1000,0	
<b>PANTONE 237 C</b>	800	TRANSPARENT BASE	519,9	
	100	WHITE	353,4	
	P301	AMC ORANGE	0,7	
	P342	AMC PINK	126,0	
			1000,0	
<b>PANTONE 238 C</b>	800	TRANSPARENT BASE	530,0	
	100	WHITE	210,0	
	P342	AMC PINK	260,0	
			1000,0	
<b>PANTONE 239 C</b>	800	TRANSPARENT BASE	578,0	
	P342	AMC PINK	420,0	
	P440	AMC VIOLET	2,0	
			1000,0	
<b>PANTONE 240 C</b>	100	WHITE	245,0	
	700	BLACK	4,0	
	P305	AMC CARMIN RED	25,0	
	P342	AMC PINK	726,0	
			1000,0	
<b>PANTONE 241 C</b>	800	TRANSPARENT BASE	98,0	
	100	WHITE	150,0	
	700	BLACK	10,0	
	P342	AMC PINK	742,0	
			1000,0	
<b>PANTONE 242 C</b>	800	TRANSPARENT BASE	168,0	
	100	WHITE	90,0	
	700	BLACK	27,0	
	P305	AMC CARMIN RED	15,0	
	P342	AMC PINK	700,0	
			1000,0	

**COLOR FORMULATING GUIDE**

**Argon® MIXING COLORS**

**FORMULATIONS FOR SIMULATIONS  
OF PANTONE® COLORS**



	<b>Ink Code</b>	<b>Color Shade</b>	<b>Weight</b>	<b>Notes</b>
<b>PANTONE 2365 C</b>	800	TRANSPARENT BASE	461,0	
	100	WHITE	507,0	
	700	BLACK	1,0	
	P301	AMC ORANGE	1,0	
	P342	AMC PINK	30,0	
			1000,0	
<b>PANTONE 2375 C</b>	800	TRANSPARENT BASE	492,0	
	100	WHITE	287,0	
	P342	AMC PINK	221,0	
			1000,0	
<b>PANTONE 2385 C</b>	800	TRANSPARENT BASE	518,4	
	P342	AMC PINK	466,7	
	P440	AMC VIOLET	14,9	
			1000,0	
<b>PANTONE 2395 C</b>	800	TRANSPARENT BASE	351,0	
	P342	AMC PINK	631,0	
	P440	AMC VIOLET	18,0	
			1000,0	
<b>PANTONE 2405 C</b>	800	TRANSPARENT BASE	200,0	
	700	BLACK	10,0	
	P342	AMC PINK	787,0	
	P404	AMC BRILLIANT BLUE	3,0	
			1000,0	
<b>PANTONE 2415 C</b>	700	BLACK	16,0	
	P342	AMC PINK	977,0	
	P404	AMC BRILLIANT BLUE	7,0	
			1000,0	
<b>PANTONE 2425 C</b>	800	TRANSPARENT BASE	348,0	
	700	BLACK	27,0	
	P342	AMC PINK	620,0	
	P404	AMC BRILLIANT BLUE	5,0	
			1000,0	

**COLOR FORMULATING GUIDE**

**Argon® MIXING COLORS**

**FORMULATIONS FOR SIMULATIONS  
OF PANTONE® COLORS**



	<b>Ink Code</b>	<b>Color Shade</b>	<b>Weight</b>	<b>Notes</b>
<b>PANTONE 243 C</b>	800	TRANSPARENT BASE	465,3	
	100	WHITE	496,3	
	P342	AMC PINK	37,5	
	P440	AMC VIOLET	0,9	
			1000,0	
<b>PANTONE 244 C</b>	800	TRANSPARENT BASE	306,8	
	100	WHITE	589,7	
	P342	AMC PINK	100,0	
	P440	AMC VIOLET	3,5	
			1000,0	
<b>PANTONE 245 C</b>	800	TRANSPARENT BASE	520,9	
	100	WHITE	338,3	
	P342	AMC PINK	135,4	
	P440	AMC VIOLET	5,4	
			1000,0	
<b>PANTONE 246 C</b>	800	TRANSPARENT BASE	607,0	
	100	WHITE	20,0	
	P342	AMC PINK	360,0	
	P440	AMC VIOLET	13,0	
			1000,0	
<b>PANTONE 247 C</b>	800	TRANSPARENT BASE	284,0	
	P342	AMC PINK	680,0	
	P440	AMC VIOLET	36,0	
			1000,0	
<b>PANTONE 248 C</b>	100	WHITE	158,6	
	P342	AMC PINK	799,0	
	P440	AMC VIOLET	42,4	
			1000,0	
<b>PANTONE 249 C</b>	100	WHITE	166,0	
	700	BLACK	34,0	
	P342	AMC PINK	800,0	
			1000,0	

**COLOR FORMULATING GUIDE**

**Argon® MIXING COLORS**

**FORMULATIONS FOR SIMULATIONS  
OF PANTONE® COLORS**



	<b>Ink Code</b>	<b>Color Shade</b>	<b>Weight</b>	<b>Notes</b>
<b>PANTONE 250 C</b>	800	TRANSPARENT BASE	480,0	
	100	WHITE	496,7	
	P200	AMC PRIMROSE YELLOW	3,7	
	P342	AMC PINK	16,5	
	P440	AMC VIOLET	3,1	
			1000,0	
<b>PANTONE 251 C</b>	800	TRANSPARENT BASE	387,0	
	100	WHITE	538,0	
	P342	AMC PINK	67,0	
	P440	AMC VIOLET	8,0	
			1000,0	
<b>PANTONE 252 C</b>	800	TRANSPARENT BASE	596,0	
	100	WHITE	250,0	
	P342	AMC PINK	139,0	
	P440	AMC VIOLET	15,0	
			1000,0	
<b>PANTONE Purple C</b>	800	TRANSPARENT BASE	658,0	
	P342	AMC PINK	315,0	
	P440	AMC VIOLET	27,0	
			1000,0	
<b>PANTONE 253 C</b>	800	TRANSPARENT BASE	286,0	
	100	WHITE	160,0	
	P342	AMC PINK	510,0	
	P440	AMC VIOLET	44,0	
			1000,0	
<b>PANTONE 254 C</b>	100	WHITE	271,0	
	P342	AMC PINK	680,6	
	P440	AMC VIOLET	48,4	
			1000,0	
<b>PANTONE 255 C</b>	100	WHITE	225,0	
	700	BLACK	25,0	
	P342	AMC PINK	720,0	
	P440	AMC VIOLET	30,0	
			1000,0	

**COLOR FORMULATING GUIDE**

**Argon® MIXING COLORS**

**FORMULATIONS FOR SIMULATIONS  
OF PANTONE® COLORS**



	<b>Ink Code</b>	<b>Color Shade</b>	<b>Weight</b>	<b>Notes</b>
<b>PANTONE 256 C</b>	800	TRANSPARENT BASE	483,5	
	100	WHITE	493,8	
	700	BLACK	2,8	
	P342	AMC PINK	17,6	
	P440	AMC VIOLET	2,3	
			1000,0	
<b>PANTONE 257 C</b>	800	TRANSPARENT BASE	461,3	
	100	WHITE	479,2	
	700	BLACK	5,0	
	P342	AMC PINK	47,4	
	P440	AMC VIOLET	7,1	
			1000,0	
<b>PANTONE 258 C</b>	800	TRANSPARENT BASE	463,6	
	100	WHITE	229,9	
	700	BLACK	13,1	
	P342	AMC PINK	247,0	
	P440	AMC VIOLET	46,4	
			1000,0	
<b>PANTONE 259 C</b>	100	WHITE	87,8	
	P342	AMC PINK	799,6	
	P440	AMC VIOLET	112,6	
			1000,0	
<b>PANTONE 260 C</b>	800	TRANSPARENT BASE	255,0	
	100	WHITE	97,0	
	700	BLACK	53,0	
	P342	AMC PINK	530,0	
	P440	AMC VIOLET	65,0	
			1000,0	
<b>PANTONE 261 C</b>	800	TRANSPARENT BASE	190,0	
	100	WHITE	120,0	
	700	BLACK	60,0	
	P342	AMC PINK	584,0	
	P440	AMC VIOLET	46,0	
			1000,0	
<b>PANTONE 262 C</b>	800	TRANSPARENT BASE	120,0	
	100	WHITE	95,0	
	700	BLACK	80,0	
	P342	AMC PINK	700,0	
	P440	AMC VIOLET	5,0	
			1000,0	



**COLOR FORMULATING GUIDE**

**Argon® MIXING COLORS**

**FORMULATIONS FOR SIMULATIONS  
OF PANTONE® COLORS**



	<b>Ink Code</b>	<b>Color Shade</b>	<b>Weight</b>	<b>Notes</b>
<b>PANTONE 2562 C</b>	800	TRANSPARENT BASE	177,5	
	100	WHITE	766,9	
	P342	AMC PINK	46,4	
	P440	AMC VIOLET	9,2	

1000,0

<b>PANTONE 2572 C</b>	800	TRANSPARENT BASE	467,6	
	100	WHITE	438,2	
	P342	AMC PINK	68,7	
	P440	AMC VIOLET	25,5	

1000,0

<b>PANTONE 2582 C</b>	800	TRANSPARENT BASE	665,6	
	100	WHITE	127,6	
	P342	AMC PINK	144,5	
	P440	AMC VIOLET	62,3	

1000,0

<b>PANTONE 2592 C</b>	800	TRANSPARENT BASE	705,0	
	P342	AMC PINK	215,0	
	P440	AMC VIOLET	80,0	

1000,0

<b>PANTONE 2602 C</b>	800	TRANSPARENT BASE	452,0	
	P342	AMC PINK	420,0	
	P440	AMC VIOLET	128,0	

1000,0

<b>PANTONE 2612 C</b>	800	TRANSPARENT BASE	315,0	
	100	WHITE	120,0	
	700	BLACK	22,0	
	P342	AMC PINK	450,0	
	P440	AMC VIOLET	93,0	

1000,0

<b>PANTONE 2622 C</b>	800	TRANSPARENT BASE	315,0	
	100	WHITE	130,0	
	700	BLACK	45,0	
	P342	AMC PINK	460,0	
	P440	AMC VIOLET	50,0	

1000,0

## COLOR FORMULATING GUIDE

# Argon® MIXING COLORS

### FORMULATIONS FOR SIMULATIONS OF PANTONE® COLORS



	Ink Code	Color Shade	Weight	Notes
<b>PANTONE 2563 C</b>	800	TRANSPARENT BASE	512,3	
	100	WHITE	465,7	
	P301	AMC ORANGE	1,4	
	P305	AMC CARMIN RED	8,1	
	P440	AMC VIOLET	12,5	
			1000,0	
<b>PANTONE 2573 C</b>	800	TRANSPARENT BASE	467,7	
	100	WHITE	466,9	
	P305	AMC CARMIN RED	29,1	
	P440	AMC VIOLET	36,3	
				1000,0
<b>PANTONE 2583 C</b>	800	TRANSPARENT BASE	164,5	
	100	WHITE	402,6	
	P342	AMC PINK	344,1	
	P440	AMC VIOLET	88,8	
				1000,0
<b>PANTONE 2593 C</b>	800	TRANSPARENT BASE	600,0	
	100	WHITE	100,0	
	P342	AMC PINK	240,0	
	P440	AMC VIOLET	60,0	
				1000,0
<b>PANTONE 2603 C</b>	100	WHITE	172,0	
	700	BLACK	6,0	
	P342	AMC PINK	697,0	
	P440	AMC VIOLET	125,0	
				1000,0
<b>PANTONE 2613 C</b>	800	TRANSPARENT BASE	284,0	
	100	WHITE	123,0	
	700	BLACK	12,0	
	P342	AMC PINK	466,0	
	P440	AMC VIOLET	115,0	
				1000,0
<b>PANTONE 2623 C</b>	800	TRANSPARENT BASE	100,0	
	100	WHITE	100,0	
	700	BLACK	25,0	
	P342	AMC PINK	670,0	
	P440	AMC VIOLET	105,0	
				1000,0

**COLOR FORMULATING GUIDE**

**Argon® MIXING COLORS**

**FORMULATIONS FOR SIMULATIONS  
OF PANTONE® COLORS**



	<b>Ink Code</b>	<b>Color Shade</b>	<b>Weight</b>	<b>Notes</b>
<b>PANTONE 2567 C</b>	800	TRANSPARENT BASE	573,0	
	100	WHITE	400,0	
	P303	AMC RED	7,0	
	P440	AMC VIOLET	20,0	

1000,0

<b>PANTONE 2577 C</b>	800	TRANSPARENT BASE	235,6	
	100	WHITE	566,9	
	P342	AMC PINK	136,3	
	P440	AMC VIOLET	61,2	

1000,0

<b>PANTONE 2587 C</b>	800	TRANSPARENT BASE	546,5	
	100	WHITE	207,8	
	P342	AMC PINK	145,9	
	P440	AMC VIOLET	99,8	

1000,00

<b>PANTONE 2597 C</b>	800	TRANSPARENT BASE	635,0	
	100	WHITE	40,0	
	P342	AMC PINK	183,0	
	P440	AMC VIOLET	142,0	

1000,0

<b>PANTONE 2607 C</b>	800	TRANSPARENT BASE	110,0	
	100	WHITE	120,0	
	P342	AMC PINK	535,0	
	P440	AMC VIOLET	235,0	

1000,0

<b>PANTONE 2617 C</b>	800	TRANSPARENT BASE	48,0	
	100	WHITE	80,0	
	700	BLACK	2,0	
	P342	AMC PINK	580,0	
	P440	AMC VIOLET	290,0	

1000,0

<b>PANTONE 2627 C</b>	800	TRANSPARENT BASE	548,0	
	100	WHITE	60,0	
	700	BLACK	27,0	
	P342	AMC PINK	235,0	
	P440	AMC VIOLET	130,0	

1000,0

**COLOR FORMULATING GUIDE**

**Argon® MIXING COLORS**

**FORMULATIONS FOR SIMULATIONS  
OF PANTONE® COLORS**



	<b>Ink Code</b>	<b>Color Shade</b>	<b>Weight</b>	<b>Notes</b>
<b>PANTONE 263 C</b>	800	TRANSPARENT BASE	501,5	
	100	WHITE	492,0	
	P202	AMC CHROME YELLOW	1,0	
	P404	AMC BRILLIANT BLUE	0,5	
	P440	AMC VIOLET	5,0	
			1000,0	
<b>PANTONE 264 C</b>	100	WHITE	975,0	
	P440	AMC VIOLET	25,0	
			1000,0	
<b>PANTONE 265 C</b>	800	TRANSPARENT BASE	554,0	
	100	WHITE	338,0	
	P440	AMC VIOLET	108,0	
			1000,0	
<b>PANTONE 266 C</b>	800	TRANSPARENT BASE	834,0	
	P342	AMC PINK	40,0	
	P404	AMC BRILLIANT BLUE	6,0	
	P440	AMC VIOLET	120,0	
			1000,0	
<b>PANTONE 267 C</b>	800	TRANSPARENT BASE	371,0	
	100	WHITE	161,0	
	P342	AMC PINK	170,0	
	P440	AMC VIOLET	298,0	
			1000,0	
<b>PANTONE 268 C</b>	800	TRANSPARENT BASE	664,0	
	100	WHITE	93,0	
	700	BLACK	38,0	
	P440	AMC VIOLET	205,0	
			1000,00	
<b>PANTONE 269 C</b>	100	WHITE	120,0	
	700	BLACK	30,0	
	P342	AMC PINK	705,0	
	P404	AMC BRILLIANT BLUE	15,0	
	P440	AMC VIOLET	130,0	
			1000,0	

**COLOR FORMULATING GUIDE**



**Argon® MIXING COLORS**

**FORMULATIONS FOR SIMULATIONS  
OF PANTONE® COLORS**

	<b>Ink Code</b>	<b>Color Shade</b>	<b>Weight</b>	<b>Notes</b>
<b>PANTONE 2635 C</b>	100	WHITE	977,0	
	P301	AMC ORANGE	1,0	
	P440	AMC VIOLET	22,0	
				1000,0
<b>PANTONE 2645 C</b>	100	WHITE	946,0	
	P301	AMC ORANGE	1,0	
	P440	AMC VIOLET	53,0	
				1000,0
<b>PANTONE 2655 C</b>	800	TRANSPARENT BASE	479,0	
	100	WHITE	430,0	
	P440	AMC VIOLET	91,0	
				1000,0
<b>PANTONE 2665 C</b>	800	TRANSPARENT BASE	719,0	
	100	WHITE	175,0	
	P440	AMC VIOLET	106,0	
				1000,0
<b>PANTONE Violet C</b>	800	TRANSPARENT BASE	833,0	
	P404	AMC BRILLIANT BLUE	7,0	
	P440	AMC VIOLET	160,0	
				1000,0
<b>PANTONE 2685 C</b>	800	TRANSPARENT BASE	639,0	
	P440	AMC VIOLET	361,0	
				1000,0
<b>PANTONE 2695 C</b>	800	TRANSPARENT BASE	233,0	
	100	WHITE	195,0	
	700	BLACK	45,0	
	P342	AMC PINK	400,0	
	P404	AMC BRILLIANT BLUE	7,0	
	P440	AMC VIOLET	120,0	
				1000,0

**COLOR FORMULATING GUIDE**

**Argon® MIXING COLORS**

**FORMULATIONS FOR SIMULATIONS  
OF PANTONE® COLORS**



	<b>Ink Code</b>	<b>Color Shade</b>	<b>Weight</b>	<b>Notes</b>
<b>PANTONE 270 C</b>	800	TRANSPARENT BASE	521,0	
	100	WHITE	459,0	
	P305	AMC CARMIN RED	14,0	
	P404	AMC BRILLIANT BLUE	6,0	
			1000,0	
<b>PANTONE 271 C</b>	800	TRANSPARENT BASE	481,0	
	100	WHITE	466,0	
	P305	AMC CARMIN RED	37,0	
	P404	AMC BRILLIANT BLUE	16,0	
			1000,0	
<b>PANTONE 272 C</b>	800	TRANSPARENT BASE	495,9	
	100	WHITE	409,9	
	P305	AMC CARMIN RED	65,8	
	P404	AMC BRILLIANT BLUE	28,4	
			1000,0	
<b>PANTONE 273 C</b>	800	TRANSPARENT BASE	390,0	
	P342	AMC PINK	540,0	
	P404	AMC BRILLIANT BLUE	53,0	
	P500	AMC GREEN	17,0	
			1000,0	
<b>PANTONE 274 C</b>	800	TRANSPARENT BASE	560,0	
	100	WHITE	42,0	
	P305	AMC CARMIN RED	78,0	
	P404	AMC BRILLIANT BLUE	100,0	
	P440	AMC VIOLET	220,0	
			1000,0	
<b>PANTONE 275 C</b>	800	TRANSPARENT BASE	160,0	
	100	WHITE	140,0	
	P305	AMC CARMIN RED	200,0	
	P404	AMC BRILLIANT BLUE	200,0	
	P440	AMC VIOLET	300,0	
			1000,0	
<b>PANTONE 276 C</b>	800	TRANSPARENT BASE	560,0	
	100	WHITE	95,0	
	700	BLACK	55,0	
	P305	AMC CARMIN RED	110,0	
	P404	AMC BRILLIANT BLUE	50,0	
	P440	AMC VIOLET	130,0	
			1000,0	

**COLOR FORMULATING GUIDE**

**Argon® MIXING COLORS**

**FORMULATIONS FOR SIMULATIONS  
OF PANTONE® COLORS**



	<b>Ink Code</b>	<b>Color Shade</b>	<b>Weight</b>	<b>Notes</b>
<b>PANTONE 2705 C</b>	800	TRANSPARENT BASE	362,7	
	100	WHITE	600,0	
	700	BLACK	0,8	
	P404	AMC BRILLIANT BLUE	4,5	
	P440	AMC VIOLET	32,0	
			1000,0	
<b>PANTONE 2715 C</b>	100	WHITE	910,0	
	P404	AMC BRILLIANT BLUE	9,0	
	P440	AMC VIOLET	81,0	
			1000,0	
<b>PANTONE 2725 C</b>	800	TRANSPARENT BASE	560,0	
	100	WHITE	300,0	
	P404	AMC BRILLIANT BLUE	10,0	
	P440	AMC VIOLET	130,0	
			1000,0	
<b>PANTONE 2735 C</b>	800	TRANSPARENT BASE	780,0	
	P404	AMC BRILLIANT BLUE	20,0	
	P440	AMC VIOLET	200,0	
			1000,0	
<b>PANTONE 2745 C</b>	800	TRANSPARENT BASE	468,0	
	100	WHITE	26,0	
	P404	AMC BRILLIANT BLUE	41,0	
	P440	AMC VIOLET	465,0	
			1000,0	
<b>PANTONE 2755 C</b>	100	WHITE	166,0	
	P404	AMC BRILLIANT BLUE	46,0	
	P440	AMC VIOLET	788,0	
			1000,0	
<b>PANTONE 2765 C</b>	800	TRANSPARENT BASE	235,0	
	100	WHITE	50,0	
	700	BLACK	15,0	
	P342	AMC PINK	460,0	
	P404	AMC BRILLIANT BLUE	40,0	
	P440	AMC VIOLET	200,0	
			1000,0	

**COLOR FORMULATING GUIDE**

**Argon® MIXING COLORS**

**FORMULATIONS FOR SIMULATIONS  
OF PANTONE® COLORS**



	<b>Ink Code</b>	<b>Color Shade</b>	<b>Weight</b>	<b>Notes</b>
<b>PANTONE 2706 C</b>	800	TRANSPARENT BASE	590,3	
	100	WHITE	400,2	
	P200	AMC PRIMROSE YELLOW	3,0	
	P404	AMC BRILLIANT BLUE	2,0	
	P440	AMC VIOLET	4,5	
			1000,0	
<b>PANTONE 2716 C</b>	800	TRANSPARENT BASE	532,0	
	100	WHITE	429,0	
	P200	AMC PRIMROSE YELLOW	5,0	
	P404	AMC BRILLIANT BLUE	9,0	
	P440	AMC VIOLET	25,0	
			1000,0	
<b>PANTONE 2726 C</b>	800	TRANSPARENT BASE	580,0	
	100	WHITE	270,0	
	P404	AMC BRILLIANT BLUE	37,0	
	P440	AMC VIOLET	113,0	
			1000,0	
<b>PANTONE 2736 C</b>	800	TRANSPARENT BASE	755,0	
	100	WHITE	110,0	
	P404	AMC BRILLIANT BLUE	30,0	
	P440	AMC VIOLET	105,0	
			1000,0	
<b>PANTONE 2746 C</b>	800	TRANSPARENT BASE	440,0	
	100	WHITE	242,0	
	P404	AMC BRILLIANT BLUE	62,0	
	P440	AMC VIOLET	256,0	
			1000,0	
<b>PANTONE 2756 C</b>	800	TRANSPARENT BASE	129,0	
	100	WHITE	328,0	
	700	BLACK	17,0	
	P404	AMC BRILLIANT BLUE	65,0	
	P440	AMC VIOLET	461,0	
			1000,0	
<b>PANTONE 2766 C</b>	100	WHITE	380,0	
	700	BLACK	90,0	
	P404	AMC BRILLIANT BLUE	50,0	
	P440	AMC VIOLET	480,0	
			1000,0	



**COLOR FORMULATING GUIDE**

**Argon® MIXING COLORS**

**FORMULATIONS FOR SIMULATIONS  
OF PANTONE® COLORS**



	<b>Ink Code</b>	<b>Color Shade</b>	<b>Weight</b>	<b>Notes</b>
<b>PANTONE 2707 C</b>	100	WHITE	986,0	
	P200	AMC PRIMROSE YELLOW	4,5	
	P404	AMC BRILLIANT BLUE	4,0	
	P440	AMC VIOLET	5,5	

1000,0

<b>PANTONE 2717 C</b>	100	WHITE	977,5	
	P200	AMC PRIMROSE YELLOW	4,0	
	P404	AMC BRILLIANT BLUE	8,0	
	P440	AMC VIOLET	10,5	

1000,0

<b>PANTONE 2727 C</b>	100	WHITE	802,0	
	P404	AMC BRILLIANT BLUE	100,0	
	P440	AMC VIOLET	98,0	

1000,0

<b>PANTONE Blue 072 C</b>	800	TRANSPARENT BASE	670,0	
	P404	AMC BRILLIANT BLUE	80,0	
	P440	AMC VIOLET	250,0	

1000,0

<b>PANTONE 2747 C</b>	800	TRANSPARENT BASE	547,0	
	100	WHITE	54,0	
	700	BLACK	45,0	
	P404	AMC BRILLIANT BLUE	134,0	
	P440	AMC VIOLET	220,0	

1000,0

<b>PANTONE 2757 C</b>	800	TRANSPARENT BASE	30,0	
	100	WHITE	210,0	
	700	BLACK	110,0	
	P404	AMC BRILLIANT BLUE	160,0	
	P440	AMC VIOLET	490,0	

1000,0

<b>PANTONE 2767 C</b>	100	WHITE	170,0	
	700	BLACK	330,0	
	P440	AMC VIOLET	500,0	

1000,0

**COLOR FORMULATING GUIDE**

**Argon® MIXING COLORS**

**FORMULATIONS FOR SIMULATIONS  
OF PANTONE® COLORS**



	<b>Ink Code</b>	<b>Color Shade</b>	<b>Weight</b>	<b>Notes</b>
<b>PANTONE 2708 C</b>	100	WHITE	984,0	
	P202	AMC CHROME YELLOW	1,0	
	P404	AMC BRILLIANT BLUE	6,0	
	P440	AMC VIOLET	9,0	
			1000,0	
<b>PANTONE 2718 C</b>	100	WHITE	881,4	
	P404	AMC BRILLIANT BLUE	49,0	
	P440	AMC VIOLET	69,6	
			1000,0	
<b>PANTONE 2728 C</b>	800	TRANSPARENT BASE	490,0	
	100	WHITE	250,0	
	P404	AMC BRILLIANT BLUE	140,0	
	P440	AMC VIOLET	120,0	
			1000,0	
<b>PANTONE 2738 C</b>	800	TRANSPARENT BASE	730,0	
	P404	AMC BRILLIANT BLUE	80,0	
	P440	AMC VIOLET	190,0	
			1000,0	
<b>PANTONE 2748 C</b>	800	TRANSPARENT BASE	110,0	
	100	WHITE	165,0	
	700	BLACK	5,0	
	P404	AMC BRILLIANT BLUE	380,0	
	P440	AMC VIOLET	340,0	
			1000,0	
<b>PANTONE 2758 C</b>	800	TRANSPARENT BASE	192,0	
	100	WHITE	50,0	
	700	BLACK	30,0	
	P404	AMC BRILLIANT BLUE	578,0	
	P440	AMC VIOLET	150,0	
			1000,0	
<b>PANTONE 2768 C</b>	800	TRANSPARENT BASE	35,0	
	100	WHITE	300,0	
	700	BLACK	120,0	
	P404	AMC BRILLIANT BLUE	145,0	
	P440	AMC VIOLET	400,0	
			1000,0	

**COLOR FORMULATING GUIDE**

**Argon® MIXING COLORS**

**FORMULATIONS FOR SIMULATIONS  
OF PANTONE® COLORS**



	<b>Ink Code</b>	<b>Color Shade</b>	<b>Weight</b>	<b>Notes</b>
<b>PANTONE 277 C</b>	100	WHITE	985,6	
	P342	AMC PINK	10,0	
	P404	AMC BRILLIANT BLUE	4,4	
			1000,0	
<b>PANTONE 278 C</b>	800	TRANSPARENT BASE	337,0	
	100	WHITE	620,0	
	700	BLACK	1,0	
	P342	AMC PINK	30,0	
	P404	AMC BRILLIANT BLUE	12,0	
			1000,0	
<b>PANTONE 279 C</b>	100	WHITE	788,0	
	P342	AMC PINK	128,0	
	P404	AMC BRILLIANT BLUE	84,0	
			1000,00	
<b>PANTONE Reflex Blue C</b>	800	TRANSPARENT BASE	680,0	
	100	WHITE	20,0	
	P404	AMC BRILLIANT BLUE	180,0	
	P440	AMC VIOLET	120,0	
			1000,0	
<b>PANTONE 280 C</b>	800	TRANSPARENT BASE	135,0	
	100	WHITE	150,0	
	700	BLACK	5,0	
	P404	AMC BRILLIANT BLUE	590,0	
	P440	AMC VIOLET	120,0	
			1000,0	
<b>PANTONE 281 C</b>	800	TRANSPARENT BASE	271,0	
	100	WHITE	112,0	
	700	BLACK	32,0	
	P404	AMC BRILLIANT BLUE	500,0	
	P440	AMC VIOLET	85,0	
			1000,0	
<b>PANTONE 282 C</b>	100	WHITE	200,0	
	700	BLACK	100,0	
	P404	AMC BRILLIANT BLUE	400,0	
	P440	AMC VIOLET	300,0	
			1000,0	

**COLOR FORMULATING GUIDE**

**Argon® MIXING COLORS**

**FORMULATIONS FOR SIMULATIONS  
OF PANTONE® COLORS**



	<b>Ink Code</b>	<b>Color Shade</b>	<b>Weight</b>	<b>Notes</b>
<b>PANTONE 283 C</b>	100	WHITE	984,0	
	P202	AMC CHROME YELLOW	1,0	
	P404	AMC BRILLIANT BLUE	9,0	
	P440	AMC VIOLET	6,0	
			1000,0	
<b>PANTONE 284 C</b>	100	WHITE	950,2	
	P202	AMC CHROME YELLOW	2,2	
	P404	AMC BRILLIANT BLUE	30,6	
	P440	AMC VIOLET	17,0	
			1000,0	
<b>PANTONE 285 C</b>	100	WHITE	736,0	
	P404	AMC BRILLIANT BLUE	199,0	
	P440	AMC VIOLET	65,0	
			1000,0	
<b>PANTONE 286 C</b>	800	TRANSPARENT BASE	640,0	
	100	WHITE	60,0	
	P404	AMC BRILLIANT BLUE	230,0	
	P440	AMC VIOLET	70,0	
			1000,0	
<b>PANTONE 287 C</b>	800	TRANSPARENT BASE	420,0	
	100	WHITE	55,0	
	700	BLACK	12,0	
	P404	AMC BRILLIANT BLUE	443,0	
	P440	AMC VIOLET	70,0	
			1000,0	
<b>PANTONE 288 C</b>	800	TRANSPARENT BASE	244,0	
	100	WHITE	53,0	
	700	BLACK	15,0	
	P404	AMC BRILLIANT BLUE	635,0	
	P440	AMC VIOLET	53,0	
			1000,0	
<b>PANTONE 289 C</b>	100	WHITE	155,0	
	700	BLACK	150,0	
	P404	AMC BRILLIANT BLUE	545,0	
	P440	AMC VIOLET	150,0	
			1000,0	

**COLOR FORMULATING GUIDE**

**Argon® MIXING COLORS**

**FORMULATIONS FOR SIMULATIONS  
OF PANTONE® COLORS**



	<b>Ink Code</b>	<b>Color Shade</b>	<b>Weight</b>	<b>Notes</b>
<b>PANTONE 290 C</b>	800	TRANSPARENT BASE	541,0	
	100	WHITE	450,0	
	P200	AMC PRIMROSE YELLOW	4,0	
	P404	AMC BRILLIANT BLUE	3,0	
	P440	AMC VIOLET	2,0	
			1000,0	
<b>PANTONE 291 C</b>	800	TRANSPARENT BASE	523,1	
	100	WHITE	459,1	
	P200	AMC PRIMROSE YELLOW	5,1	
	P404	AMC BRILLIANT BLUE	8,1	
	P440	AMC VIOLET	4,6	
			1000,0	
<b>PANTONE 292 C</b>	800	TRANSPARENT BASE	537,8	
	100	WHITE	425,0	
	P200	AMC PRIMROSE YELLOW	6,1	
	P404	AMC BRILLIANT BLUE	21,0	
	P440	AMC VIOLET	10,1	
			1000,0	
<b>PANTONE 293 C</b>	800	TRANSPARENT BASE	570,0	
	100	WHITE	140,0	
	P404	AMC BRILLIANT BLUE	250,0	
	P440	AMC VIOLET	40,0	
			1000,0	
<b>PANTONE 294 C</b>	800	TRANSPARENT BASE	289,0	
	100	WHITE	70,0	
	700	BLACK	20,0	
	P404	AMC BRILLIANT BLUE	587,0	
	P440	AMC VIOLET	34,0	
			1000,0	
<b>PANTONE 295 C</b>	800	TRANSPARENT BASE	95,0	
	100	WHITE	124,0	
	700	BLACK	45,0	
	P404	AMC BRILLIANT BLUE	721,0	
	P440	AMC VIOLET	15,0	
			1000,0	
<b>PANTONE 296 C</b>	100	WHITE	306,0	
	700	BLACK	262,0	
	P404	AMC BRILLIANT BLUE	322,0	
	P440	AMC VIOLET	110,0	
			1000,0	

**COLOR FORMULATING GUIDE**

**Argon® MIXING COLORS**

**FORMULATIONS FOR SIMULATIONS  
OF PANTONE® COLORS**



	<b>Ink Code</b>	<b>Color Shade</b>	<b>Weight</b>	<b>Notes</b>
<b>PANTONE 2905 C</b>	800	TRANSPARENT BASE	561,0	
	100	WHITE	420,0	
	P200	AMC PRIMROSE YELLOW	5,0	
	P404	AMC BRILLIANT BLUE	10,0	
	P440	AMC VIOLET	4,0	
			1000,0	
<b>PANTONE 2915 C</b>	800	TRANSPARENT BASE	532,2	
	100	WHITE	421,8	
	P200	AMC PRIMROSE YELLOW	6,9	
	P404	AMC BRILLIANT BLUE	31,3	
	P440	AMC VIOLET	7,8	
			1000,0	
<b>PANTONE 2925 C</b>	800	TRANSPARENT BASE	495,7	
	100	WHITE	397,3	
	P200	AMC PRIMROSE YELLOW	4,4	
	P404	AMC BRILLIANT BLUE	91,3	
	P440	AMC VIOLET	11,3	
			1000,0	
<b>PANTONE 2935 C</b>	800	TRANSPARENT BASE	655,0	
	100	WHITE	140,0	
	P404	AMC BRILLIANT BLUE	180,0	
	P440	AMC VIOLET	25,0	
			1000,0	
<b>PANTONE 2945 C</b>	100	WHITE	457,0	
	700	BLACK	12,0	
	P404	AMC BRILLIANT BLUE	496,0	
	P440	AMC VIOLET	35,0	
			1000,0	
<b>PANTONE 2955 C</b>	100	WHITE	365,0	
	700	BLACK	70,0	
	P404	AMC BRILLIANT BLUE	515,0	
	P440	AMC VIOLET	50,0	
			1000,0	
<b>PANTONE 2965 C</b>	100	WHITE	329,0	
	700	BLACK	207,0	
	P404	AMC BRILLIANT BLUE	429,0	
	P440	AMC VIOLET	35,0	
			1000,0	

## COLOR FORMULATING GUIDE

# Argon® MIXING COLORS

### FORMULATIONS FOR SIMULATIONS OF PANTONE® COLORS



	Ink Code	Color Shade	Weight	Notes
<b>PANTONE 297 C</b>	800	TRANSPARENT BASE	537,4	
	100	WHITE	446,2	
	P200	AMC PRIMROSE YELLOW	1,1	
	P404	AMC BRILLIANT BLUE	12,9	
	P440	AMC VIOLET	2,4	
			1000,0	
<b>PANTONE 298 C</b>	800	TRANSPARENT BASE	534,2	
	100	WHITE	423,0	
	P200	AMC PRIMROSE YELLOW	4,9	
	P404	AMC BRILLIANT BLUE	33,6	
	P440	AMC VIOLET	4,3	
			1000,0	
<b>PANTONE 299 C</b>	800	TRANSPARENT BASE	516,5	
	100	WHITE	406,2	
	P200	AMC PRIMROSE YELLOW	5,0	
	P404	AMC BRILLIANT BLUE	66,6	
	P440	AMC VIOLET	5,7	
			1000,0	
<b>PANTONE 300 C</b>	800	TRANSPARENT BASE	568,0	
	100	WHITE	190,0	
	P404	AMC BRILLIANT BLUE	235,0	
	P440	AMC VIOLET	7,0	
			1000,0	
<b>PANTONE 301 C</b>	100	WHITE	310,0	
	700	BLACK	12,0	
	P404	AMC BRILLIANT BLUE	678,0	
			1000,0	
<b>PANTONE 302 C</b>	100	WHITE	411,7	
	700	BLACK	85,6	
	P404	AMC BRILLIANT BLUE	496,3	
	P440	AMC VIOLET	6,4	
			1000,0	
<b>PANTONE 303 C</b>	100	WHITE	422,0	
	700	BLACK	191,0	
	P202	AMC CHROME YELLOW	6,0	
	P404	AMC BRILLIANT BLUE	381,0	
			1000,0	

**COLOR FORMULATING GUIDE**

**Argon® MIXING COLORS**

**FORMULATIONS FOR SIMULATIONS  
OF PANTONE® COLORS**



	<b>Ink Code</b>	<b>Color Shade</b>	<b>Weight</b>	<b>Notes</b>
<b>PANTONE 2975 C</b>	800	TRANSPARENT BASE	494,0	
	100	WHITE	500,0	
	P404	AMC BRILLIANT BLUE	6,0	
				1000,0
<b>PANTONE 2985 C</b>	800	TRANSPARENT BASE	257,0	
	100	WHITE	708,0	
	700	BLACK	2,0	
	P404	AMC BRILLIANT BLUE	33,0	
			1000,0	
<b>PANTONE 2995 C</b>	800	TRANSPARENT BASE	510,0	
	100	WHITE	390,0	
	P404	AMC BRILLIANT BLUE	92,0	
	P500	AMC GREEN	8,0	
			1000,0	
<b>PANTONE 3005 C</b>	800	TRANSPARENT BASE	585,0	
	100	WHITE	200,0	
	P404	AMC BRILLIANT BLUE	215,0	
			1000,0	
<b>PANTONE 3015 C</b>	800	TRANSPARENT BASE	322,0	
	100	WHITE	333,0	
	700	BLACK	7,0	
	P404	AMC BRILLIANT BLUE	300,0	
	P500	AMC GREEN	38,0	
			1000,0	
<b>PANTONE 3025 C</b>	100	WHITE	372,7	
	700	BLACK	62,9	
	P404	AMC BRILLIANT BLUE	482,2	
	P500	AMC GREEN	82,2	
			1000,0	
<b>PANTONE 3035 C</b>	100	WHITE	383,0	
	700	BLACK	183,0	
	P200	AMC PRIMROSE YELLOW	105,0	
	P404	AMC BRILLIANT BLUE	329,0	
			1000,0	



**COLOR FORMULATING GUIDE**

**Argon® MIXING COLORS**

**FORMULATIONS FOR SIMULATIONS  
OF PANTONE® COLORS**



	<b>Ink Code</b>	<b>Color Shade</b>	<b>Weight</b>	<b>Notes</b>
<b>PANTONE 304 C</b>	800	TRANSPARENT BASE	511,8	
	100	WHITE	475,4	
	P200	AMC PRIMROSE YELLOW	5,3	
	P342	AMC PINK	0,6	
	P404	AMC BRILLIANT BLUE	6,9	
			1000,0	
<b>PANTONE 305 C</b>	800	TRANSPARENT BASE	275,0	
	100	WHITE	695,0	
	P200	AMC PRIMROSE YELLOW	7,0	
	P404	AMC BRILLIANT BLUE	23,0	
			1000,0	
<b>PANTONE 306 C</b>	800	TRANSPARENT BASE	517,1	
	100	WHITE	417,7	
	P200	AMC PRIMROSE YELLOW	10,5	
	P404	AMC BRILLIANT BLUE	54,7	
			1000,0	
<b>PANTONE Process Blue C</b>	800	TRANSPARENT BASE	770,0	
	100	WHITE	100,0	
	P404	AMC BRILLIANT BLUE	120,0	
	P500	AMC GREEN	10,0	
			1000,0	
<b>PANTONE 307 C</b>	800	TRANSPARENT BASE	635,0	
	100	WHITE	67,0	
	P404	AMC BRILLIANT BLUE	246,0	
	P500	AMC GREEN	52,0	
			1000,0	
<b>PANTONE 308 C</b>	800	TRANSPARENT BASE	335,0	
	100	WHITE	84,0	
	700	BLACK	16,0	
	P404	AMC BRILLIANT BLUE	422,0	
	P500	AMC GREEN	143,0	
			1000,0	
<b>PANTONE 309 C</b>	100	WHITE	265,0	
	700	BLACK	135,0	
	P404	AMC BRILLIANT BLUE	340,0	
	P500	AMC GREEN	260,0	
			1000,0	